METALOR®

Au Ag

Data Sheet

Alloy code:	10038	**Colour:**	White
General Description:	9ct standard white gold alloy, for universal use. It can easily be cupped, stamped, rolled, polished, drawn and machined. Suitable for casting in air.		

Other properties:



Density - g/cm³:	12,55	
Melting range:	1030 - 1070 °C	
Composition:	AU:37,60% AG: 55,47%	
Pickling:	Hot 10% sulphuric acid	
Hardness - HV5:	95	*Annealed*

Casting data:



Flask Temp.	≈ 600 °C	
Casting Temp.	1170 - 1270 °C	
Cooling:	Air cooling	
Hardness - HV5:	90	*Post cast*

Recommended Solder:



Description:	Melting range:	Material code
9 White Gold Solder MEDIUM	735°C-755°C	300018233

Available profiles:



Grain

Disclaimer; Although we try to assure accuracy, Metalor cannot be responsible for typographical error on our data sheets.
Images & drawings are for illustrative purposes only and may not necessarily portray actual items sold.

Metalor Technologies (UK) Ltd - 74, Warstone Lane - GB-Birmingham B18 6NG
Phone: +44(0)121 262 3090 - Fax: +44(0)121 236 3568 - Email: watch.uk@metalor.com