

6. TECHNICAL INFORMATION

The following tables outline the key technical information on Anticon products. Further information can be found on the product data sheets available from the Bradford website www.bradfordinsulation.com.au

6.1. Dimensions and Weights

Product	Base Blanket Material R-Value R_{MAT}	Thickness (mm)	Nominal Length (m)	Nominal Width (mm)	Nominal Coverage per roll (m ²)	Nominal Density (kg/m ³)	Nominal Pack Weight (kg)
ANTICON							
Anticon 55	R1.3	60	15	1200	18	10	11.88
Anticon 55	R1.3	60	15	1400	21	10	13.86
Anticon 75	R1.8	80	15	1200	18	11	15.84
Anticon 95	R2.3	100	10	1200	12	11	13.2
Anticon 110	R2.5	110	10	1200	12	11	14.52
Anticon 100HP	R2.5	100	10	1200	12	14	16.8
Anticon 130	R3.0	130	10	1200	12	12	17.16
ACOUSTICON							
Acousticon	R1.5	75	15	1200	18	9	14.85
AGRICON							
Agricon	R1.5	75	15	1200	18	9	14.85

6.2. Physical Properties

Property	Product	Test	Result
Maximum Service Temperature	Glasswool Base blanket Facings: Foil Ultrapon		350°C 70°C 300°C
Moisture Absorption	All products	4 days @50C and 95% RH	Less than 0.2% by volume
Compliance with Standards	All products	AS/NZS4859.1 "Materials for the Thermal Insulation of Buildings"	Complies