

Table 1 - Classification of COLORBOND® steel Colours for BCA and BASIX for the COLORBOND® steel Standard 22 Colours

Colour	Solar Absorptance	BCA Classification	BASIX Classification
Cove™	0.54	M	M
Mangrove®	0.64	D	M
Gully™	0.63	D	M
Wallaby®	0.64	D	M
Terrain®	0.69	D	M
Basalt®	0.69	D	M
Nightsky®	0.96	D	D
Classic Cream™	0.32	L	L
Surfmist®	0.32	L	L
Paperbark®	0.42	M	L
Evening Haze®	0.43	M	L
Shale Grey™	0.43	M	L
Dune®	0.47	M	L
Windspray®	0.58	M	M
Pale Eucalypt®	0.60	M	M
Jasper®	0.68	D	M
Manor Red®	0.69	D	M
Woodland Grey®	0.71	D	D

Monument®	0.73	D	D
Ironstone®	0.74	D	D
Cottage Green®	0.75	D	D
Deep Ocean®	0.75	D	D

Table 2 - Classification of COLORBOND® Metallic steel for BCA and BASIX

Colour	Solar Absorptance	BCA Classification	BASIX Classification
Galactic™	0.34	L	L
Cosmic™	0.39	L	L
Rhea™	0.49	M	M
Astro®	0.62	D	M
Aries™	0.70	D	M
Celestian™	0.93	D	D

Table 3 - Classification of COLORBOND® Coolmax® steel for BCA and BASIX

Colour	Solar Absorptance	BCA Classification	BASIX Classification
Whitehaven®	0.23	L	L

Notes:

1. ZINCALUME® steel is not included in the Tables above. Unpainted metal coated roofs, such as ZINCALUME® steel, have a low thermal emittance so perform differently to conventional painted surfaces (high emittance) from both an energy efficiency basis and impact upon urban heating. For the purpose of BCA and NSW BASIX ZINCALUME® steel should be considered a medium colour (per ASTM E1980).