

Optical & Solar Properties

Single Glazing				
Sheet Description	LT	ST	SR	SHGC
DP4mm Clear	89%	80%	17%	0.81
DP4mm Blue*	64%	73%	17%	0.75
DP4mm Bronze*	38%	41%	12%	0.50
DP4mm Grey	41%	51%	12%	0.58
DP4mm Reflective Grey	20%	18%	33%	0.28
DP8mm Clear	71%	60%	36%	0.61
DP8mm Blue	50%	57%	27%	0.60
DP8mm Bronze	25%	26%	18%	0.37
DP8mm Green	60%	52%	32%	0.55
DP8mm Grey	30%	35%	22%	0.44
DP8mm Ice	60%	54%	32%	0.57
DP8mm Opal	35%	38%	40%	0.42
DP8mm Dark Opal*	20%	22%	54%	0.27
DP8mm Reflective Grey	20%	18%	33%	0.28
DP10mm Clear	71%	60%	36%	0.61
DP10mm Blue	50%	57%	27%	0.60
DP10mm Bronze	25%	26%	18%	0.37
DP10mm Green	60%	52%	32%	0.55
DP10mm Grey	30%	35%	22%	0.44
DP10mm Ice	60%	54%	32%	0.57
DP10mm Opal	35%	38%	40%	0.42
DP10mm Orange	40%	45%	15%	0.52
DP10mm Dark Opal	20%	22%	54%	0.27
DP10mm Reflective Grey	20%	18%	33%	0.28
DP10mm Yellow	58%	52%	26%	0.56
DP16mm Clear*	63%	51%	40%	0.53
DP16mm Blue*	49%	51%	38%	0.53
DP16mm Bronze*	35%	35%	30%	0.42
DP16mm Green*	44%	42%	33%	0.47
DP16mm Grey*	31%	38%	30%	0.44
DP16mm Ice	51%	50%	38%	0.52
DP16mm Opal	22%	28%	51%	0.32
DP16mm Orange*	36%	39%	24%	0.46
DP16mm Dark Opal*				
DP16mm Reflective Grey	20%	18%	33%	0.28
DP16mm Yellow*	50%	45%	26%	0.45

Optical & Solar Properties

Double Glazing					
Exterior	Interior	LT	ST	SR	SHGC
DP8 Opal	DP8 Ice*	20%	26%	48%	0.312
DP8 Reflective Grey	DP8 Ice*	13%	13%	27%	0.250
DP8 Reflective Grey	DP8 Reflective Grey	4.50%	5%	25%	0.190
DP8 Reflective Grey	DP8 Opal	7.50%	9.50%	26%	0.224
DP10 Clear	DP8 Ice	42%	41%	36%	0.456
DP10 Clear	DP8 Clear	50%	46%	33%	0.502
DP10 Clear	DP8 Opal	26%	30%	44%	0.352
DP10 Clear	DP8 Green*	38%	37%	32%	0.432
DP10 Clear	DP8 Blue*	26%	38%	30%	0.444
DP10 Clear	DP8 Dark Opal Softlite*	14%	21%	51%	0.266
DP10 Ice	DP8 Clear	40%	40%	35%	0.450
DP10 Ice	DP8 Ice	35%	37%	37%	0.422
DP10 Ice	DP8 Opal	21%	27%	47%	0.322
DP10 Ice	DP8 Green*	29%	30%	33%	0.374
DP10 Ice	DP8 Dark Opal Softlite*	12%	19%	49%	0.254
DP10 Opal	DP8 Clear	25%	29%	46%	0.340
DP10 Opal	DP8 Ice*	21%	27%	48%	0.320
DP10 Opal	DP8 Opal	14%	21%	49%	0.270
DP10 Opal	DP8 Dark Opal Softlite*	8%	16%	54%	0.220
DP10 Green	DP8 Clear	39%	38%	23%	0.458
DP10 Green	DP8 Ice*	33%	34%	25%	0.422
DP10 Green	DP8 Opal	20%	24%	30%	0.332
DP10 Green	DP8 Green	30%	30%	23%	0.394
DP10 Green	DP8 Dark Opal Softlite*	9%	17%	34%	0.268
DP10 Bronze	DP8 Clear	16%	19%	13%	0.326
DP10 Bronze	DP8 Ice*	14%	16%	13%	0.302
DP10 Bronze	DP8 Opal	8%	12%	15%	0.266
DP10 Bronze	DP8 Bronze	6%	8%	12%	0.240
DP10 Bronze	DP 8 Reflective Grey	5%	6%	14%	0.220
DP10 Bronze	DP8 Dark Opal Softlite*	4%	10%	16%	0.248
DP10 Dark Opal	DP8 Clear	15%	19%	55%	0.242
DP10 Dark Opal	DP8 Ice	13%	18%	55%	0.234
DP10 Dark Opal	DP8 Opal	9%	14%	56%	0.200
DP10 Dark Opal	DP8 Dark Opal Softlite*	5%	13%	58%	0.188
DP10 Blue	DP8 Clear	28%	38%	23%	0.458
DP10 Blue	DP8 Ice	24%	35%	27%	0.426
DP10 Blue	DP8 Opal	14%	25%	33%	0.334
DP10 Blue	DP8 Blue	16%	34%	28%	0.416
DP10 Blue	DP8 Dark Opal Softlite*	8%	18%	38%	0.268

Optical & Solar Properties

Double Glazing Continued		LT	ST	SR	SHGC
DP10 Reflective Grey	DP8 Clear	15%	14%	25%	0.262
DP10 Reflective Grey	DP8 Ice	13%	12%	25%	0.246
DP10 Reflective Grey	DP8 Opal	8%	9%	26%	0.220
DP10 Reflective Grey	DP8 Reflective Grey	5%	4.50%	25%	0.186
DP10 Reflective Grey	DP8 Dark Opal Softlite*	5%	7%	5%	0.246
DP12 Reflective Grey	DP10 Opal	8%	10%		0.280
DP12 Reflective Grey	DP10 Ice	13%	12%		0.296
DP12 Reflective Grey	DP10 Clear	15%	14%		0.312
DP16 Ice	DP16 Ice	23%	27%	40%	0.336
DP16 Opal	DP16 Opal	7%	14%	49%	0.214
DP16 Clear*	DP16 Clear*	37%	37%	36%	0.424
DP16 Ice	DP16 Clear*	27%	31%	38%	0.372
DP16 Blue*	DP16 Ice	21%	30%	38%	0.364
DP16 Blue*	DP16 Blue*	21%	29%	27%	0.378
DP16 Opal	DP16 Clear	12%	18%	51%	0.242
DP16 Reflective Grey	DP16 Ice	9%	11%	20%	0.248
DP16 Ice	DP16 Reflective Grey	8%	9%	35%	0.202

LT% of visible light transmission (400 – 700 nm)

ST% of total solar radiation transmission (300 – 2800 nm)

SR% of total solar reflection (300 – 2800 nm)

SHGC-Solar Heat Gain Coefficient, total solar energy transmitted through the panel

= %ST+0.2X[1-(%ST+%SR)]

Softlite	LT	ST	SR	SHGC
DP12mm Ice Softlite	56%	57%	30%	0.57
DP16mm Clear Softlite*	53%	50%	35%	0.52
DP16mm Blue Softlite*	42%	46%	31%	0.50
DP16mm Green Softlite*	34%	35%	25%	0.43
DP16mm Ice Softlite	40%	41%	38%	0.45
DP16mm Reflective Grey Softlite*	20%	17%	29%	0.28

Danpalon® Softlite (matt finish) nulls the neon effect phenomenon particularly for the bright colours (Clear, Blue, Green and Ice). The Softlite solution can be added to all Danpalon® colours on either one or both sides of the panels.

* Items not stocked in Australia. An 8-12 week lead times and production surcharges may apply.