KKS Phase Field Model of Precipitate Evolution coupled with nucleation

March 19, 2024

The Nucleation Model application for PRISMS-PF incorporates a stochastic method to add nuclei to the KKS phase field model for precipitate growth. Nuclei are seeded throughout the time evolution of the system based on a probability that depends on the local solute supersaturation. This document is divided in two sections. In the first section, the phase field model formulation for precipitate evolution in a binary alloy (without elastic effects) is presented. In the second section the nucleation method is presented.

1 Precipitate Evolution

1.1 Variational formulation

In the absence of elastic effects total free energy of the 2-component system (neglecting boundary terms) is of the form,

$$\Pi(c,\eta) = \int_{\Omega} f(c,\eta) \ dV \tag{1}$$

where c is the concentration of the β phase and η is the set of structural order parameters. The free energy density, f, is given by

$$f(c,\eta) = f_{chem}(c,\eta) + f_{grad}(\eta)$$
(2)

where

$$f_{chem}(c,\eta) = f_{\alpha}(c,\eta) \left(1 - H(\eta)\right) + f_{\beta}(c,\eta)H(\eta) + W f_{Landau}(\eta)$$
(3)

and

$$f_{grad}(\eta) = \frac{1}{2}\kappa |\nabla \eta|^2 \tag{4}$$

In the KKS model (Kim 1999), the interfacial region is modeled as a mixture of the α and β phases with concentrations c_{α} and c_{β} , respectively. The homogenous free energies for each phase, f_{α} and f_{β} in this case, are typically given as functions of c_{α} and c_{β} , rather than directly as functions of c and η_p . Thus, $f_{chem}(c,\eta)$ can be rewritten as

$$f_{chem}(c,\eta) = f_{\alpha}(c_{\alpha}) \left(1 - H(\eta)\right) + f_{\beta}(c_{\beta})H(\eta) + W f_{Landau}(\eta)$$
(5)

The concentration in each phase is determined by the following system of equations:

$$c = c_{\alpha} \left(1 - H(\eta) \right) + c_{\beta} H(\eta) \tag{6}$$

$$\frac{\partial f_{\alpha}(c_{\alpha})}{\partial c_{\alpha}} = \frac{\partial f_{\beta}(c_{\beta})}{\partial c_{\beta}} \tag{7}$$

Given the following parabolic functions for the single-phase homogenous free energies:

$$f_{\alpha}(c_{\alpha}) = A_2 c_{\alpha}^2 + A_1 c_{\alpha} + A_0 \tag{8}$$

$$f_{\beta}(c_{\beta}) = B_2 c_{\beta}^2 + B_1 c_{\beta} + B_0 \tag{9}$$

the single-phase concentrations are:

$$c_{\alpha} = \frac{B_2 c + \frac{1}{2} (B_1 - A_1) H(\eta)}{A_2 H(\eta) + B_2 (1 - H(\eta))}$$
(10)

$$c_{\beta} = \frac{A_2 c + \frac{1}{2} (A_1 - B_1) [1 - H(\eta)]}{A_2 H(\eta) + B_2 [1 - H(\eta)]}$$
(11)

1.2 Required inputs

- $f_{\alpha}(c_{\alpha}), f_{\beta}(c_{\beta})$ Homogeneous chemical free energy of the components of the binary system, example form given above
- $f_{Landau}(\eta)$ Landau free energy term that controls the interfacial energy. Example form given in Appendix I
- W Barrier height for the Landau free energy term, used to control the thickness of the interface
- $H(\eta)$ Interpolation function for connecting the α phase and the β phase. Example form given in Appendix I
- κ^{η_p} gradient penalty coefficient for the $\alpha \beta$ interface

In addition, to drive the kinetics, we need:

- ullet M mobility value for the concentration field
- \bullet L mobility value for the structural order parameter field

1.3 Variational treatment

We obtain chemical potentials for the concentration and the structural order parameter by taking variational derivatives of Π :

$$\mu_c = f_{\alpha,c} \left(1 - H(\eta) \right) + f_{\beta,c} H(\eta) \tag{12}$$

$$\mu_{\eta} = \left[f_{\beta} - f_{\alpha} - (c_{\beta} - c_{\alpha}) f_{\beta, c_{\beta}} \right] H(\eta)_{,\eta} + W f_{Landau,\eta} - \kappa \eta \tag{13}$$

1.4 Kinetics

Now the PDE for Cahn-Hilliard dynamics is given by:

$$\frac{\partial c}{\partial t} = \nabla \cdot \left(\frac{1}{f_{,cc}} M \nabla \mu_c \right) \tag{14}$$

where M is a constant mobility and the factor of $\frac{1}{f,cc}$ is added to guarentee constant diffusivity in the two phases. The PDE for Allen-Cahn dynamics is given by:

$$\frac{\partial \eta}{\partial t} = -L\mu_{\eta_p} \tag{15}$$

where L is a constant mobility.

1.5 Time discretization

Using forward Euler explicit time stepping, equations 14 and 15 become:

$$c^{n+1} = c^n + \Delta t \left[\nabla \cdot \left(\frac{1}{f_{,cc}} M \nabla \mu_c \right) \right]$$
 (16)

$$\eta_p^{n+1} = \eta_p^n - \Delta t L \mu_{\eta_p} \tag{17}$$

1.6 Weak formulation

Writing equations 14 and 15 in the weak form, with the arbitrary variation given by w yields:

$$\int_{\Omega} wc^{n+1}dV = \int_{\Omega} wc^n + w\Delta t \left[\nabla \cdot \left(\frac{1}{f_{,cc}} M \nabla \mu_c \right) \right] dV$$
(18)

$$\int_{\Omega} w \eta^{n+1} dV = \int_{\Omega} w \eta^n - w \Delta t L \mu_{\eta} dV \tag{19}$$

The expression of $\frac{1}{f_{cc}}\mu_c$ can be written as:

$$\frac{1}{f_{,cc}}\nabla\mu_c = \nabla c + (c_\alpha - c_\beta)H(\eta)_{,\eta}\nabla\eta \tag{20}$$

Applying the divergence theorem to equation 18, one can derive the residual terms r_c and r_{cx} :

$$\int_{\Omega} wc^{n+1}dV = \int_{\Omega} w \underbrace{c^n}_{r_c} + \nabla w \cdot (\underbrace{-\Delta t M \frac{1}{f_{,cc}} \nabla \mu_c}) dV$$
(21)

Expanding μ_{η} in equation 19 and applying the divergence theorem yields the residual terms r_{η} and $r_{\eta x}$:

$$\int_{\Omega} w \eta^{n+1} dV = \int_{\Omega} w \left\{ \underbrace{\eta^n - \Delta t L \left[(f_{\beta} - f_{\alpha}) H(\eta^n)_{,\eta} - (c_{\beta} - c_{\alpha}) f_{\beta,c_{\beta}} H(\eta^n)_{,\eta} + W f_{Landau,\eta} \right]}_{r_{\eta}} \right.$$

$$+ \nabla w \cdot \underbrace{\left(-\Delta t L \kappa \eta^n \right)}_{r_{\eta x}} dV \tag{22}$$

2 Nucleation method

We follow the same approach as Jokisaari and Thornton [Comput. Mater. Sci. 112, 128-138 (2016)] which consists of adding nuclei throughout a phase field simulation based on a probability that depends on the local supersaturation. This probability is calculated every fixed number of time steps and for every element of the computational domain. In each nucleation event, nucleation is triggered at a point within the α phase. Each nucleus is then added to the system by modifying the order parameter to it's β phase value within a small domain around the selected nucleation center. This domain can be spherical/circular or ellipsoidal/elliptical.

2.1 Nucleation rate

From classical nucleation theory, the nucleation rate for critical nuclei J^* is given by

$$J^*(\mathbf{r},t) = Zn\beta^* \exp\left(-\frac{\Delta G^*}{k_B T}\right) \exp\left(-\frac{\tau}{t}\right),\tag{23}$$

where Z is the Zeldovich factor, n is the number of nucleation sites per volume, β^* is the frequency at which a critical nucleus becomes supercritical, ΔG^* is the nucleation energy barrier, k_B is the Boltzmann constant, T is the temperature, t is time and τ is the incubation time. It can be shown that, in the dilute limit and for constant temperature, Eq. (23) can be simplified by grouping approximately constant terms in both the exponential and pre-exponential factors:

$$J^*(\mathbf{r},t) = k_1 \exp\left(-\frac{k_2}{(\Delta c)^{d-1}}\right) \exp\left(-\frac{\tau}{t}\right),\tag{24}$$

where k_1 and k_2 are now taken as constant parameters, $\Delta c = c(\mathbf{r}, t) - c_{\alpha}^{eq}$ is the local supersaturation in the α phase and d is the dimensionality of the system (e.g. d = 2 or d = 3).

2.2 Nucleation probability

Considering J^* to be approximately constant within a small volume, ΔV , and for a small time interval, Δt , the probability that at least one nucleation event occurs in ΔV within Δt is given by [Simmons et al., Scripta Mater. 43, 935 (2000)]

$$P(\mathbf{r},t) = 1 - \exp\left(-J^* \Delta V \Delta t\right) \tag{25}$$

2.3 Hold time

After each nucleus is added, there is a 'hold' time interval, Δt_h , during which the order parameter value is fixed within a small window that encompasses the new nucleus. The purpose of this hold time is to allow the concentration to evolve within the nucleus to a value close to the coexistance composition for β phase, and therefore, to create small a solute depleted zone around the nucleus. After the hold time, the nucleus is allowed to evolve into a precipitate.

2.4 Required nucleation inputs

- k_1 Constant pre-exponential factor in Eq. (24)
- k_2 Parameter that groups all constant terms of the first exponential factor in Eq. (24)
- τ Incubation time constant in Eq. (24)
- Δt_h Nucleation hold time.

Dimensions (ellipsoidal semiaxes) of precipitate seeds

- a semiaxis in the x-direction
- b semiaxis in the y-direction
- c semiaxis in the x-direction

Appendix I: Example functions for f_{α} , f_{β} , f_{Landau} , $H(\eta)$

$$f_{\alpha}(c_{\alpha}) = A_2 c_{\alpha}^2 + A_1 c_{\alpha} + A_0 \tag{26}$$

$$f_{\beta}(c_{\beta}) = B_2 c_{\beta}^2 + B_1 c_{\beta} + B_0 \tag{27}$$

$$f_{Landau}(\eta) = \eta^2 - 2\eta^3 + \eta^4 \tag{28}$$

$$H(\eta) = 3\eta^2 - 2\eta^3 \tag{29}$$