

University of Lagos
Metallurgical & Materials Engineering Laboratory

Tensile Test Report

Customer Name :
Material Name :
Test Speed


AIS063
5.000mm/min

Operator :
Test Standard :
Gauge Length :

Pogson
ASTM E8
50.000mm

Test Period
Specifications

7/1/2026 9:31



No.	Offset (mm)	Thickness (mm)	Width (mm)	Area (F _{0.2}) (%)	Tensile Strength (MPa)	Elongation percentage @ break (%)	Strain (F _{0.2}) (mm/mm)	Elasticity Coef (F _{0.2}) (mm)	Young's Modulus (MPa)	Strength @ upper yield point (MPa)	
1	0	1.55	12.25	98.988	178.647	18.755	8.468	988.787	2258.561	189.428	
2	0	1.49	12.25	98.872	161.752	14.988	6.488	933.166	2288.871	178.284	
3	0	1.55	12.1	98.825	173.717	20.28	9.284	931.352	2282.862	187.161	
4	0	1.5	12	98.8	173.178	15.888	6.734	988.332	2333.898	187.893	
5	0	1.5	12.1	98.828	184.288	11.513	5.47	744.748	2851.648	184.225	
Mean	-	-	-	-	173.812	16.471	7.529	877.689	2291.884	182.818	