


University of Lagos
Metallurgical & Materials Engineering Laboratory

Tensile Test Report

Customer Name : Operator : Pogoso Test Period 6/30/2026 13:57
Material Name : PA12 XY Test Standard : ASTM D638 Specifications
Test Speed 5.000mm/min Gauge Length: 25.000mm



No.	OutDia.(mm)	Thickness(mm)	Width(mm)	Force @ Peak(N)	Tensile Stress(MPa)	elongation percentage @ break(%)	Elong. @ Peak(mm)	ElasticityCoe.(N/mm)	Yong's Modulus(MPa)	Strength @ upper yield point(MPa)
1	0	3.51	6.42	1101.288	48.872	38.418	9.429	125.82	139.589	21.977
2	0	3.47	6.4	1086.577	48.927	31.457	7.619	191.676	215.774	44.511
3	0	3.47	6.38	1069.906	48.327	35.683	8.732	155.706	175.828	45.492
4	0	3.5	6.37	1086.578	48.736	34.684	8.316	176.849	198.305	43.326
Mean	-	-	-	1086.087	48.715	35.06	8.524	162.513	182.374	38.827