


University of Lagos
Metallurgical & Materials Engineering Laboratory

Tensile Test Report

Customer Name : Operator : Pogeson Test Period 6/30/2026 19:04
Material Name : PETG CF XY Test Standard : ASTM D638 Specifications
Test Speed 5.000mm/min Gauge Length: 25.000mm



No.	OutDia.(mm)	Thickness(mm)	Width(mm)	Force @ Peak(N)	Tensile Stress(MPa)	elongation percentage @ break(%)	Elong. @ Peak(mm)	ElasticityCoe.(N/mm)	Yong's Modulus(MPa)	Strength @ upper yield point(MPa)
1	0	3.4	6.3	963.994	45.004	27.674	3.802	273.887	319.674	20.236
2	0	3.45	6.33	950.264	43.514	22.871	3.934	279.689	320.186	43.29
3	0	3.45	6.35	946.342	43.198	19.894	3.525	309.461	353.153	43.153
4	0	3.47	6.35	963.013	43.704	21.529	3.769	289.604	328.573	19.627
5	0	3.45	6.3	959.091	44.127	20.86	3.794	291.438	335.218	19.852
Mean	-	-	-	956.541	43.909	22.566	3.765	288.818	331.361	29.232