


University of Lagos
Metallurgical & Materials Engineering Laboratory

Tensile Test Report

Customer Name : Operator : Pogoson Test Period 6/30/2026 19:40
Material Name : PETG CF ZX Test Standard : ASTM D638 Specifications
Test Speed 5.000mm/min Gauge Length : 25.000mm



No.	OutDia.(mm)	Thickness(mm)	Width(mm)	Force @ Peak(N)	Tensile Stress(MPa)	elongation percentage @ break(%)	Elong. @ Peak(mm)	ElasticityCoe.(N/mm)	Yong's Modules(MPa)	Strength @ upper yield point(MPa)	
1	0	3.5	6.1	54.918	2.572	3.064	0.746	96.517	113.017	1.929	
2	0	3.75	6.2	313.813	13.497	8.497	2.093	122.794	132.036	6.074	
3	0	3.5	6.1	117.68	5.512	4.752	1.174	74.332	87.04	2.434	
4	0	3.47	6.05	176.52	8.408	6.324	1.571	83.492	99.424	3.737	
5	0	3.5	6.1	118.661	5.558	5.285	1.291	99.364	116.351	4.547	
Mean	-	-	-	156.318	7.109	5.584	1.375	95.3	109.574	3.744	