

Computational screening of sustainable low-emissivity PVD coatings on soda-lime float glass

Technical report Saint-Gobain Research India Author: Varun Mandy, Research Intern
Framework: [pvdlowe](#) v0.1.0 — <https://github.com/VarunMandy/pvdlowe>

Abstract

A computational framework was developed to execute the screening workflow set out in the project brief *PVD_Usecase.docx*: element screening, thermodynamic stability, optical multilayer modelling, design of experiments and multi-objective ranking, for cost-effective low-emissivity coatings deposited by argon magnetron sputtering.

Applying the framework to the brief produced three classes of result. First, the proposed multi-objective weighting was found to contain four defects, one of which allowed a thickness optimiser to return a design consuming 29% *more* silver than the incumbent while scoring 100/100. Second, two of the brief's literature citations could not be matched to any locatable source, and one pivotal measurement was found inconsistent with a model-independent electrodynamic limit. Thermodynamic screening of all fifteen nominated chemical systems confirmed that Ag-Cu possesses no stable ordered compound, supporting the brief's suspicion of phase separation with first-principles evidence. Third, the design-space search identified a material class and a stack architecture outside the brief's framing, both of which outperform the proposed candidates: silicon nitride dielectrics improve visible transmittance by up to nine percentage points over AZO, and the composition optimum lies at 5-15 at.% Ag rather than the proposed 70%.

No films were deposited. All performance figures are model outputs. The framework's own validation identifies its largest error — an approximately eightfold under-prediction of sputtered copper sheet resistance — in the material on which most leading candidates depend. A specified experiment resolving this, with pre-registered decision rules and an automated analysis path, is delivered with the framework. A subsequent literature review narrowed the cause without deposition: no published surface- or grain-boundary-scattering parameters account for the discrepancy, whereas a nanocrystalline grain structure does — reducing the decisive measurement from an eight-film series to a single X-ray diffraction scan.

1. Scope and deliverables

1.1 What was asked

The brief proposed a materials-by-design programme for transparent low-emissivity coatings on float glass, centred on a dielectric/metal/dielectric architecture (AZO/metal/AZO) and asking how much silver could be removed while retaining visible transmittance, sheet resistance and far-infrared reflectance.

1.2 What was delivered

Deliverable	Status
Computational framework implementing the brief's \$21 workflow	Complete — 12,000 lines, 92 tests
Element and compound screening	Complete
Optical multilayer model (transfer matrix, EN 410 / 673 / 12898)	Complete, validated
Thin-film transport model coupled to optics	Complete, uncalibrated — requires \$6 experiment
Multi-objective scoring with provenance grading	Complete
Design of experiments generator	Complete
DFT input generation (VASP)	Complete, not executed — requires VASP licence and HPC allocation
Materials Project integration	Complete and executed — 15/15 systems retrieved
Candidate ranking, 38 architectures	Complete, model outputs only
Experimental protocol with pre-registered analysis	Complete, not executed — requires tool access
Illuminant sensitivity quantified	Complete (\$7.3)
Manufacturability constraints	Complete
Triple-metal architecture search	Complete — negative result (\$5.4)

Repository, documentation, results and protocols are version-controlled and archived to [gs://sg-llamole-pvdlowe/pvdlowe/source/](https://sg-llamole-pvdlowe/pvdlowe/source/) .

1.3 What was not done, and why

No depositions were performed. The author did not have sputter tool access during the internship period. The experimental work is therefore specified rather than executed, and the protocol in §6 is written as a handover document that a colleague with tool access can run without further input.

2. The framework

2.1 Physical model

Optics. A vectorised transfer-matrix solver handles arbitrary layer counts, complex refractive indices, both polarisations and oblique incidence. Thick glass is treated incoherently. Verified against exact Fresnel reflectance for a bare interface, exact null for a quarter-wave antireflection layer, and energy conservation to 10^{-10} on absorbing stacks.

Optical constants. Metals use the Lorentz-Drude parameterisation of Rakić et al. (1998), with one deliberate departure: the free-electron damping is re-anchored to DC resistivity rather than taken from the published optical fit. Rakić's fitted Γ_0 for silver implies $\rho \approx 4.4 \mu\Omega\cdot\text{cm}$ against a true 1.587, because in the visible the Drude term trades off against interband oscillators. Using the published value and then applying a thin-film size-effect multiplier double-counts the same scattering, and inflated modelled emissivity roughly threefold in an early build.

Transport. Full Fuchs-Sondheimer integral for surface scattering, Mayadas-Shatzkes for grain boundaries, and a percolation model below a critical thickness. Critically, the resulting resistivity ratio **feeds back into the Drude damping**: a film too thin to conduct is automatically a film that reflects poorly. Without this coupling, optimising for transmittance drives the metal thickness to zero and reports an excellent coating.

Standards integration. EN 410 / ISO 9050 for visible and solar transmittance; EN 12898 for normal emissivity, weighted by a 283 K Planck radiance; EN 673 for the hemispherical correction and centre-pane U-value, cross-checked against direct angular integration.

2.2 Provenance grading

Every physical quantity carries an evidence grade — MEASURED, LITERATURE, LITERATURE_UNVERIFIED, MP_API, DFT_OWN, MODEL, CALIBRATED, ESTIMATE, HYPOTHESIS — and a guard function refuses to admit HYPOTHESIS-grade values into headline tables without explicit opt-in.

This implements the brief's own caution ("I would not yet put numerical DFT values for $\text{Ag}_{70}\text{Cu}_{29}\text{Ti}_1$ into a thesis as if they were established facts") as a type constraint rather than a footnote, so the distinction survives contact with a spreadsheet.

3. Method audit: the multi-objective weighting

The brief's §14 specifies criteria and weights for ranking candidates. Encoding that table literally produced a scoring function that did not measure the project's stated objective. Four issues were identified by the framework's own diagnostics ([pvdlowe check-weights](#)). All are documented decisions in [data/targets.yaml](#) ; none is a silent change.

3.1 Silver consumption carried zero weight

The §14 table contains no line for silver consumption, although §17 and §20 both name minimising it as an objective. In the literal encoding, silver mass was computed, displayed, and reported as the limiting criterion, but contributed nothing to the score.

The thickness optimiser exploited this immediately, returning a 12.84 nm design using **0.135 g/m² of silver — 29% more than the incumbent benchmark — at a score of 100/100.**

Correction applied: weight 0.15.

3.2 Emissivity and sheet resistance double-count one property

Across the candidate set these correlate at $r = 0.996$, because both are the free-carrier response of the same metal layer. The §14 weights of 0.25 and 0.15 therefore place 0.40 of the total on a single physical quantity.

Correction applied: sheet resistance weighted 0.0 and reported as a constraint. This should be reversed (with emissivity reduced to 0.15) if the coating is also required to function as a transparent electrode, where sheet resistance is an independent objective.

The same diagnostic flags cost against supply risk ($r = 0.993$) and silver mass against cost ($r = 1.000$ — silver dominates metal cost so completely that they are the same quantity in different units).

3.3 Targets set at the specification minimum, causing saturation

Derringer-Suich desirability saturates at 1.0 once a target is reached. Setting the visible-transmittance target to 0.80 — the brief's *floor of acceptability* — made the criterion flat exactly where candidates differ.

The consequence was measurable: across 181 oxide-thickness combinations clearing $T_{\text{vis}} = 0.80$, transmittance spanned 0.800 to 0.881 while the **score decreased** from 74.99 to 73.30. The optimiser satisfied at the specification floor and drove the top oxide to 15 nm, a thickness that would not survive handling.

Correction applied: targets set as aspirations (T_{vis} 0.90, ϵ_h 0.02). Re-optimising then returned AZO 25 / Ag 10 / AZO 35 nm at T_{vis} 0.880 — eight points better on identical silver.

General principle: a desirability target should be an aspiration, not a specification minimum.

3.4 The supply-risk band could not discriminate

With floor 8.0 against candidate values of 4.5–7.5, all silver-bearing compositions scored 0.1–0.28 and supply risk was reported as limiting for 12 of 14 candidates.

Correction applied: floor 9.5, target 4.0 — still zeroing indium-bearing ITO, which is the criterion's purpose.

3.5 Aggregation

The brief states its weighting should prevent a candidate "winning simply because it has excellent conductivity while being unacceptable optically". A weighted arithmetic sum does not achieve this — a candidate scoring zero on one criterion forfeits only that criterion's weight. A geometric mean does.

Under the corrected weighting the pure-silver benchmark ranks 4th under arithmetic aggregation and 7th under geometric; pure copper ranks 1st and 2nd respectively. These are precisely the two candidates the brief is concerned with comparing. The framework defaults to geometric and reports both.

3.6 Note on interpreting the diagnostics

The `limiting_criterion` field is `argmin(desirability)` — where a candidate is weakest, not what drives the ordering. Under geometric aggregation, whichever criterion sits nearest its floor is reported as limiting for every candidate. The appropriate test of whether weights are doing work is the weight-sensitivity analysis: before these corrections, one candidate won 97.5% of randomised weightings with a rank standard deviation of 0.16, which indicates the weights had no effect rather than that the result was robust.

4. Evidence audit

Eight literature benchmarks were transcribed from the brief. **All eight sources have been located. One has been read in full text**; the remainder are paywalled and confirmed only against their published abstracts.

State	Count
Fully verified (full text read, measurement basis confirmed)	1
Partial (source identified, figures confirmed against abstract)	5
Disputed (located sources do not contain the quoted figures)	2
Not located	0

Two further sources outside the brief's citation list have also been read in full: Cueva & Carretero (*Coatings* **13**, 1709, 2023), which corrected the dielectric model in §5.2, and the four Cu scattering-parameter studies underpinning §6.1. Both are open access.

Run `pvdlowe provenance` for the live state; the counts above are generated from `data/benchmarks.yaml` and will change as verification proceeds.

4.1 Two citations could not be supported

The figures **85.4% T_{vis} / 3.21 Ω/sq / 97% FIR** and **78.7% T_{vis} / 2.7 Ω/sq** appear in neither located AZO/Ag/AZO study. A companion PET-substrate paper reports 78.5% with 91% FIR at 10 nm Ag — close to one, but a different substrate and a different figure.

Recommendation: these two entries should not be cited pending identification of their source. Both are flagged `disputed` in the framework.

A corollary worth recording: these two entries are the model's three closest agreements (0.3%, 1.0%, 1.2% relative error). Excluding them, the median validation error rises from 14.7% to 30.6%. The framework's apparent accuracy rested partly on figures that cannot be traced.

4.2 A pivotal measurement is physically inconsistent

Applied Surface Science **578** (2022) 152051 reports AZO(40)/Cu/AZO(40) with T_{vis} 87.7%, R_s 9.96 Ω/sq and ϵ 0.055. The brief's §16 concludes from this that a silver-free stack may already meet a low-emissivity target — a conclusion that reframes the

entire programme.

The transcription is accurate and the abstract attributes all three values to one sample. However, for a conducting sheet thin compared with the wavelength, far-infrared reflectance is fixed by sheet resistance alone:

$$r = (n_1 - n_2 - Z_0/R_s) / (n_1 + n_2 + Z_0/R_s), \quad \epsilon = 1 - r^2$$

with $Z_0 = 376.73 \, \Omega$. No fitted parameter enters. At $9.96 \, \Omega/\text{sq}$ this gives $\epsilon \geq \mathbf{0.096}$; the reported 0.055 would require approximately $5.5 \, \Omega/\text{sq}$.

Four candidate explanations were tested and eliminated:

Explanation	Outcome
Values from different samples	Abstract attributes all three to one sample
Transcription error	Confirmed against published abstract
Far-IR glass index assumption	Limit is 0.091–0.097 across $n = 1.5$ to 4.0
Band-limited emissometer (8–14 μm)	Reads 5–8% higher, not lower — moves it the wrong way
The framework's own convention	An industrial formula in use since 2000 gives the same answer

The band-emissometer hypothesis was the most plausible and was tested by implementing band-limited emissivity in the framework. For a Drude metal, reflectance is nearly flat across 5–14 μm and the 283 K Planck weighting already peaks near 10 μm , so restricting the band removes the 5–8 μm region where these stacks reflect slightly less well. Correcting for measurement basis therefore *worsens* the discrepancy, from 0.58 to 0.53 of the limit.

The same group reports $\epsilon = 0.045$ at $8.10 \, \Omega/\text{sq}$ and $\epsilon = 0.050$ at comparable sheet resistance. Three measurements at a consistent 0.57–0.63 of the electrodynamic limit indicates a systematic effect rather than an isolated error.

Independent corroboration. Cueva & Carretero compute emissivity from sheet resistance as $\epsilon_n = 0.0106 \cdot R_{\square}$, citing Gläser, *Large Area Glass Coating* (Von Ardenne, 2000) — a reference in industrial use for two decades. That relation and the impedance limit derived here agree within 10% across 2–17 Ω/sq . At $9.96 \, \Omega/\text{sq}$ the industrial formula gives **0.106**, against this framework's 0.096 and the reported 0.055 — a ratio of **0.52**. The objection that the discrepancy might be an artifact of the framework's convention is therefore answered: two independent methods, one derived from first principles and one in commercial use, agree.

Untested: hemispherical versus normal basis (which would also raise the reading), instrument calibration, or the two quantities being measured on different areas of one nominal sample.

Recommendation: obtain the full text and establish the measurement basis before §16's conclusion is used. This is the single highest-value literature action outstanding.

4.3 A reported thin-film resistivity that cannot be correct

A 2025 study reports ~10 nm films of Ag at $1.59 \, \mu\Omega\cdot\text{cm}$, Ag–Cu at 2.97 and Cu at 20.5, deposited under identical conditions.

Film	Reported	× bulk	Framework model
Ag, 10 nm	$1.59 \, \mu\Omega\cdot\text{cm}$	1.00×	$4.44 \, \mu\Omega\cdot\text{cm}$ (2.79×
Cu, 10 nm	$20.5 \, \mu\Omega\cdot\text{cm}$	12.2×	$7.11 \, \mu\Omega\cdot\text{cm}$ (4.23×

Silver's electron mean free path is 53 nm; a 10 nm film cannot reach bulk resistivity, and Fuchs–Sondheimer alone forces a ratio above approximately 2. The stated thickness uncertainty ($\pm 2.5 \, \text{nm}$) does not resolve this: the upper bound is still 1.25× bulk. Under identical deposition, the copper film shows a strong size effect and the silver film shows none.

Consequence for the brief. §7 argues that amorphous Ag–Cu retains unusually good conductivity by comparing 2.97 against 1.59. If the silver baseline is not like-for-like, the comparison should be made against the copper value (20.5), against which the alloy appears sevenfold better — the argument survives in stronger form.

4.4 Three factual corrections

- **Deposition methods differ across the benchmark set.** The AZO/Ag/AZO trilayers used RF magnetron sputtering (§3 implies DC); the AZO single-layer study used medium-frequency sputtering. Film density and resistivity do not transfer between techniques and these sources should not be pooled.
- ~~The AZO visible transmittance is 81.4%, not 82.4%.~~ **Retracted — see §4.5.** The paper reports both figures in different sections; the brief quoted the Results value and was right to.
- **§7's resistivity table mixes measurement conventions**, per §4.3 above.

4.5 The one fully verified source, and a retraction

Mazur et al., *Materials* **17**(1), 81 (2024), DOI 10.3390/ma17010081 — the AZO single-layer benchmark — is open access and has been read in full.

Confirmed: resistivity $2.6 \times 10^{-3} \Omega\text{-cm}$; optical band gap 3.12 eV by Tauc for allowed indirect transitions; hardness 11.4 GPa; reduced modulus 98 GPa; sheet resistance 68 Ω/sq . The band gap had been unchecked until now.

A correction is retracted. §4.4 of an earlier version of this report recorded that the brief's 82.4% visible transmittance was a transcription error for 81.4%. **That was wrong.** The paper reports both: §3.1 gives the average transparency over 360–760 nm as 82.4%, while the abstract and conclusions give 81.4%. The source is internally inconsistent, and the brief quoted the Results figure — which is defensible. The error was introduced by checking only the abstract, which is precisely the shortcut the [partial](#) grade exists to flag.

Two facts established that are not in the brief. The film thickness is $380 \pm 5 \text{ nm}$ by optical profilometry, which independently confirms the framework's inference from ρ/R_s and means this resistivity is not transferable to the 30–40 nm layers used inside a multilayer. And the crystallite sizes by Scherrer are 14.0 nm (ZnO 002), 17.7 nm (Al_2O_3 023) and 16.2 nm (Al_2ZnO_4 220) — roughly $0.04 \times$ the film thickness, with the authors attributing the unusually high hardness to that nanocrystalline structure via Hall–Petch. **Strongly nanocrystalline growth is therefore normal for magnetron-sputtered oxide films**, which supports the grain-size hypothesis in §6.1.

Deposition was medium-frequency pulsed magnetron sputtering, on fused silica and Corning glass — not soda-lime float glass.

4.6 What verification confirmed elsewhere

The *Ceramics International* study states that far-infrared reflectance was measured by FTIR spectroscopy and sheet resistance by four-point probe — a spectroscopic reflectance directly comparable with the framework's convention, with no emissometer ambiguity. This is consistent with the model reproducing that benchmark to 0.4%, its closest agreement against a traceable source.

It also independently supports the percolation anchor: silver continuity at 10 nm is confirmed by XRD (200 and 220 reflections), which is structural evidence rather than an inference from a resistivity discontinuity.

5. Design-space results

Thirty-eight candidate architectures were evaluated; 58 metal systems screened; a 168-point composition series run across two microstructure models, two dielectrics and two climate profiles.

5.1 The composition optimum lies at 5–15 at.% Ag

Eight composition curves were generated with stack geometry re-optimised at every composition (Ag 0–100% in 5% steps).

Profile	Microstructure	Dielectric	Optimum Ag	Score	Plateau
Heating	Segregated	Si_3N_4	0.05	89.3	0.00–0.20
Heating	Solid solution	Si_3N_4	0.00	88.9	0.00
Heating	Segregated	AZO	0.10	76.5	0.05–0.40
Heating	Solid solution	AZO	0.00	74.4	0.00–0.05
Cooling	Either	AZO	0.00	68.2	0.00–0.15
Cooling	Either	Si_3N_4	0.00	67.6	0.00–0.10

Every curve peaks between 0 and 10 at.% Ag. The brief's $\text{Ag}_{70}\text{Cu}_{30}$ priority composition is outperformed in all eight combinations.

This is a sustainability result, not a performance one. Emissivity and sheet resistance continue improving to 50 at.% Ag (0.0386 and 2.59 Ω/sq , the best in the series). The score declines because silver mass carries weight. The trade is approximately 0.005 in emissivity for an 87% reduction in silver, and it is the correct trade only under the premise that silver consumption matters.

Plateau width is more relevant to process capability than peak position. The segregated/AZO curve is flat from 5 to 40 at.% Ag — a wide composition tolerance. Solid-solution curves are sharp (0–5%).

The unresolved microstructure question loses importance in the dilute regime. At $\text{Ag}_{70}\text{Cu}_{30}$ the two hypotheses differ by 9–14 points; at $\text{Ag}_5\text{Cu}_{95}$ by 2.5. Designing at 5–15 at.% Ag makes the programme robust to a question that is currently unsettled, rather than dependent on it.

5.2 The dielectric choice matters, through metal nucleation rather than optics

This section was revised after experimental comparison. An earlier version concluded that silicon nitride outperforms AZO on optical grounds. That conclusion is contradicted by measurement, the model has been corrected, and the correction is recorded here rather than applied silently.

The measurement. Cueva & Carretero (*Coatings* **13**, 1709, 2023, open access, full text read) deposited five dielectrics under identical conditions on a semi-industrial inline sputtering system with 10 nm Ag:

Dielectric	Measured ϵ	n(550 nm)
SnO ₂	0.083	2.00
ZnO	0.064	2.019
AZO	0.058	1.85
SiAlN _x	0.067	2.09

AZO gives the lowest emissivity *and* the better visible transmission (86.8% against 81.9% for SnO₂), despite having the **lowest** refractive index of the set. The authors attribute this to silver growth being more efficient on AZO.

The framework's error. It modelled the dielectric purely as an interference layer — index and thickness — and therefore preferred the higher-index nitride. The optical inputs were sound; their measured indices match the framework's closely. What was missing is that the underlayer determines the *quality of the metal grown on it*.

The correction. A `metal_growth_factor` per dielectric now applies a resistivity penalty, calibrated to that series and normalised to AZO = 1.00: ZnO 1.10, SiAlN_x 1.16, ITO 1.20, TiO₂ 1.25, SnO₂ 1.43. The model now reproduces the measured ordering and the magnitudes to within 4–8%.

What this implies more broadly. This is the same class of omission as the copper sheet-resistance discrepancy in §6: the framework models ideal metal layers, while the dominant effect in practice is underlayer-dependent metal microstructure. Two independent findings now converge on that gap, and any successor should treat nucleation quality as a first-class parameter.

The productive outcome: a hybrid stack. AZO beneath for nucleation, nitride above for durability through tempering — which is what industry does, and which the same authors measured as giving *better* emissivity than two AZO layers, because nitride deposited over the Ti barrier converts part of it to TiN_x. Two candidates were added on this basis:

ID	Stack	T _{vis}	ϵ_h	R _s	Heating score
H1	AZO/Ag/Si ₃ N ₄	0.918	0.057	4.30	67.4
M0	AZO/Ag/AZO (benchmark)	0.876	0.060	4.18	65.0
H2	AZO/Cu/Si ₃ N ₄ (silver-free)	0.788	0.042	2.93	79.9
M6	AZO/Cu/AZO	0.738	0.046	2.87	69.6

H1 beats the benchmark on transmittance and emissivity simultaneously. H2 gains five points of transmittance over the pure-AZO copper stack at lower emissivity, and remains silver-free.

5.2b Superseded analysis: index matching

An initial screen of 58 metal systems at fixed AZO thickness found that **only pure silver met the full specification**; copper failed on transmittance alone (0.752 against 0.80). Allowing the dielectric to vary changed this:

Metal	AZO	SnO ₂	TiO ₂	Si ₃ N ₄
Cu	0.755	0.795	0.786	0.845
Cu ₉₀ Zn ₁₀	0.772	0.808	0.780	0.836
Ag ₇₀ Cu ₃₀	0.837	0.869	0.835	0.912
Ag	0.880	0.902	0.868	0.923

Silicon nitride gains **nine percentage points of visible transmittance on copper** — the margin that was disqualifying it. All metals improve, indicating a dielectric property rather than a copper-specific effect.

Notably, **the highest-index material does not win**: TiO₂ (n = 2.45) underperforms SnO₂ (n = 2.00). Antireflection around a metal layer is an *index-matching* problem, not an *index-maximisation* problem.

Why this was outside the brief's framing. The brief's screening began from the periodic table and the Materials Project, both of which surface oxides. Nitrides fall outside that search structure. Silicon nitride is nonetheless the industry-standard Low-E dielectric — dense, an effective diffusion barrier, and durable through tempering — and it blocks the oxygen ingress that is copper's dominant degradation pathway, which is precisely why the Cu/Si₃N₄ pairing is attractive and why it does not appear in the AZO literature.

Lattice absorption was checked and found negligible. Si₃N₄ absorbs near 11.7 μ m, within the thermal band, so far-infrared phonon oscillators were added to the model. The penalty on the copper stack is +0.0007 in emissivity (1.7% relative), because at 10 μ m the copper layer reflects approximately 96% of the incident field and little reaches the nitride.

5.3 Climate reverses the ranking

The brief does not specify a climate, and `targets.yaml` as derived from it does not constrain solar heat gain. That omission encodes a heating-dominated assumption. Adding the EN 410 / ISO 9050 metrics:

$$g = T_{\text{sol}} + N \cdot A_{\text{sol}} \quad (N = 0.36 \text{ for a coating on surface 2})$$

$$\text{LSG} = T_{\text{vis}} / g$$

Candidate	Heating	Rank	Cooling	Rank	g	LSG
Si ₃ N ₄ /Ag ₁₀ Cu ₉₀ /Si ₃ N ₄	89.3	1	50.4	20	0.760	1.16
Si ₃ N ₄ /Cu/Si ₃ N ₄	88.9	3	55.5	12	0.731	1.18
AZO/Cu/AZO	69.6	15	65.4	1	0.558	1.32
AZO/Ag/AZO (benchmark)	65.0	22	53.0	17	0.646	1.35

The mechanism is physical, not a scoring artifact. **AZO is a transparent conductive oxide**: its free carriers give a screened plasma wavelength at 1.25 μm, inside the solar band. Si₃N₄ is a passive insulator, transparent throughout.

λ (nm)	1200	1600	2000	2400
Transmittance, AZO stack	0.240	0.115	0.068	0.046
Transmittance, Si ₃ N ₄ stack	0.509	0.259	0.151	0.099

Same 11 nm copper layer in both. **The conductive oxide performs solar-control work that a passive nitride cannot.** \$5.2 read AZO's near-infrared absorption purely as a transmittance penalty; a substantial part of it is a solar-control benefit that the heating-weighted objective could not see.

For Indian architectural glazing this is decisive, and the recommended material differs from the heating-climate case. A results table should not be circulated without its weighting profile attached.

5.4 Single-metal architectures cannot achieve solar control

The best light-to-solar-gain ratio across all 38 candidates is **1.37**, against approximately 2.0 for commercial solar-control glazing. Under the cooling profile, no single-metal stack met the transmittance target.

Generalising the framework to n metal layers separated by n+1 dielectrics:

Architecture	Metal	Dielectric	Geometry (nm)	T_vis	g	LSG	ε_h	R_s
Single	Cu	AZO	45/12/45	0.738	0.558	1.32	0.0463	2.87
Double	Ag	Si₃N₄	15/12/60/12/15	0.819	0.464	1.76	0.0248	1.67
Double	Cu	Si ₃ N ₄	59/13/105/13/59	0.716	0.516	1.39	0.0244	1.33

LSG 1.76 against a single-metal ceiling of 1.37 — a 28% improvement.

A single metal film trades transmittance against infrared reflectance along one curve; thickness moves along that curve but not off it. The dielectric *between* two metal layers introduces an interference degree of freedom, allowing the two metal reflections to cancel in the visible while adding in the infrared. This degree of freedom does not exist with one metal layer at any thickness or composition — the limitation is architectural, and no compositional search could have revealed it.

A third metal layer was tested and is not worth adding. Scanning n = 1, 2, 3 against the cooling profile, the second layer buys a large gain and the third almost none:

n	Ag/Si ₃ N ₄ LSG	Ag (g/m²)	Cu/Si ₃ N ₄ cooling score
1	1.33	0.115	67.3
2	1.76	0.252	68.9
3	1.81	0.315	37.2

The third layer adds 0.05 in LSG for a 25% increase in silver, and for copper it is actively harmful — transmittance collapses to 0.437 and the cooling score halves. **The architecture argument stops at two layers for this specification.** Commercial triple-silver products reach LSG ≈ 2.0 using asymmetric layer thicknesses and tuned interlayer spacing that this coarse scan did not explore; that remains open, but it is a fine-optimisation question rather than an architectural one.

Costs are real. Silver consumption doubles, since each layer must independently exceed percolation near 10 nm. Splitting a film also raises resistance: two 12 nm layers are not equivalent to one 24 nm layer, each carrying its own surface scattering. Process complexity rises to five layers.

Of most interest for the Indian application: the double-copper Si₃N₄ stack achieves LSG 1.39 at R_s 1.33 Ω/sq and ε_h 0.0244 with **zero silver**, scoring 68.9 on the cooling profile — the highest of any candidate evaluated. Its sheet resistance and emissivity are the best figures the framework has produced. Transmittance at 0.716 remains short of 0.80, but the deficit has narrowed from 12 points to 8 and the dielectric search was coarse.

5.5 Thermodynamic screening (Materials Project)

All fifteen chemical systems nominated in the brief's §9 were retrieved and screened for phases within 50 meV/atom of the convex hull.

The central result: Ag-Cu has no stable ordered compound. Two intermediate phases exist and neither lies on the hull:

Phase	E above hull	Stable
Cu ₃ Ag	0.0904 eV/atom	No
CuAg ₃	0.0857 eV/atom	No

Ag-Cu is thermodynamically a **phase-separating system** — which the brief's §5 suspected from the 13% lattice mismatch, and which is now supported by first-principles data rather than inferred. The magnitude matters: 86–90 meV/atom is well above k_{BT} at deposition (26 meV at 300 K, 48 meV at 550 K), so the driving force to separate is substantial rather than marginal.

What this does and does not establish. It is an equilibrium statement. A magnetron-sputtered film is quenched from the vapour at effective rates that routinely trap metastable solid solutions, so it does not predict the as-deposited microstructure. It predicts what the film will do on annealing — which is precisely the discriminating experiment of §8.3, and it indicates the direction to expect: resistivity should *fall* as copper precipitates from a trapped solution.

It also lends thermodynamic support to the segregated microstructure model, under which §5.1's dilute-silver optimum is strongest.

Ag-Cu is the only nominated binary with no stable intermediate phase:

System	Entries	Near-hull	Representative phases
Ag-Cu	2	0	— (phase-separating)
Ag-Ti	4	2	Ti ₂ Ag, TiAg
Al-Cu	15	10	Al ₂ Cu, AlCu, AlCu ₃
Cu-Ti	12	8	TiCu, TiCu ₂ , Ti ₂ Cu
Al-Zn-O	4	2	Al ₂ ZnO ₄ , Al ₁₀ ZnO ₁₆
Cu-O	37	9	Cu ₂ O, CuO, Cu ₄ O ₃
Ag-O	18	11	Ag ₂ O, AgO, Ag ₃ O
Ag-Cu-O	7	4	CuAgO ₂ , Cu ₂ Ag ₂ O ₃

This adds a mechanism to the dilute-stabiliser finding in §5.7. Both Cu-Ti and Al-Cu are richly intermetallic — eight and ten near-hull phases respectively. A dilute Ti or Al addition to a Cu-bearing film therefore has stable compounds available to form, so on annealing it is more likely to precipitate an intermetallic than to remain in solution acting as a stabiliser. That is a second reason for the ternary underperforming, independent of the conductivity penalty.

Ag-Cu-O is also populated (four near-hull phases including CuAgO₂), which bears on durability: an Ag-Cu film that oxidises has stable ternary oxides available, not merely a mixture of Ag₂O and CuO.

Limitation. The Materials Project holds DFT results for ordered crystalline phases at 0 K. It cannot describe a disordered sputtered solid solution, thin-film optical constants at 10 nm, or interface energies against an amorphous oxide. The framework records this limitation per query rather than leaving it implicit.

5.6 Ranked candidates

All 38 architectures were scored under both climate profiles. **The two top-ten lists share exactly one candidate.** This is the practical form of §5.3: the climate is not a refinement to the ranking, it selects a different design space.

The single exception is instructive. **H2, the AZO/Cu/Si₃N₄ hybrid, appears in both** — 9th on the heating profile and 2nd on cooling. It is the only architecture in the set that combines a conductive-oxide underlayer (for solar-NIR rejection, which the cooling profile rewards) with a nitride overlayer (for transmittance and durability, which the heating profile rewards). Before the §5.2 nucleation correction, no candidate did both, and the lists were fully disjoint. That a hybrid is the only design robust to the climate question is a result in its own right.

Columns: geometry as bottom/metal/top in nm; g is the EN 410 solar heat gain coefficient; LSG = T_{vis}/g ; "spec" is $T_{\text{vis}} \geq 0.80$, $R_{\text{s}} \leq 5 \text{ } \Omega/\text{sq}$, $\epsilon_{\text{h}} \leq 0.10$.

Heating-dominated (Northern Europe) — [data/targets.yaml](#)

#	ID	Architecture	Geometry	T_vis	ϵ_h	R_s	g	LSG	Ag g/m ²	\$/m ²	Score	Spec
1	E5e	Si3N4/Ag5Cu95/Si3N4 (segregated)	59/11/48	0.863	0.0481	2.98	0.731	1.18	0.008	0.07	88.1	yes
2	E10e	Si3N4/Ag10Cu90/Si3N4 (segregated)	59/10/48	0.877	0.0511	3.13	0.758	1.16	0.015	0.12	88.1	yes
3	N6	Si3N4/Cu/Si3N4	60/11/50	0.858	0.0538	3.41	0.729	1.18	0.000	0.01	87.5	yes
4	E5	Si3N4/Ag5Cu95/Si3N4	59/11/48	0.861	0.0609	3.99	0.728	1.18	0.008	0.07	85.1	yes
5	N7	Si3N4/Cu90Zn10/Si3N4	60/11/50	0.850	0.0695	4.66	0.725	1.17	0.000	0.01	83.0	yes
6	E10	Si3N4/Ag10Cu90/Si3N4	59/11/48	0.864	0.0670	4.50	0.729	1.19	0.016	0.14	83.0	yes
7	N8	Si3N4/Cu90Ag10/Si3N4	60/11/50	0.863	0.0671	4.50	0.730	1.18	0.016	0.14	82.9	yes
8	N35e	Si3N4/Ag60Cu40/Si3N4 (segregated)	45/9/40	0.902	0.0498	3.04	0.793	1.14	0.065	0.53	80.7	yes
9	H2	AZO/Cu/Si3N4 (hybrid, silver-free)	40/12/40	0.788	0.0425	2.93	0.631	1.25	0.000	0.01	79.9	no
10	N3e	Si3N4/Ag70Cu30/Si3N4 (segregated)	25/9/35	0.899	0.0508	3.16	0.769	1.17	0.073	0.59	78.1	yes
—	M0	AZO/Ag/AZO (benchmark)	35/10/35	0.876	0.0603	4.18	0.646	1.35	0.105	0.85	65.0	yes

Nine of ten use silicon nitride; the exception is the AZO/Cu/Si₃N₄ hybrid (H2) introduced by the \$5.2 correction. 9 of ten meet the full specification, and 8 of ten use less than 0.05 g/m² of silver against the benchmark's 0.105. The leading candidate uses **one thirteenth of the benchmark's silver** while beating it on emissivity and sheet resistance.

Note these figures moved when the nucleation correction of \$5.2 was applied: emissivities rose by roughly 5–12% for the nitride stacks, since Si₃N₄ carries a growth-factor penalty of 1.16 against AZO's 1.00. The ordering within the nitride family was not disturbed, but the margin over AZO narrowed.

Cooling-dominated (India) — [data/targets_cooling.yaml](#)

#	ID	Architecture	Geometry	T_vis	ϵ_h	R_s	g	LSG	Ag g/m ²	\$/m ²	Score	Spec
1	M6	AZO/Cu/AZO (low-cost control)	35/12/35	0.738	0.0463	2.87	0.558	1.32	0.000	0.01	65.4	no
2	H2	AZO/Cu/Si3N4 (hybrid, silver-free)	40/12/40	0.788	0.0425	2.93	0.631	1.25	0.000	0.01	63.4	no
3	D10e	AZO/Ag10Cu90/AZO (segregated)	15/9/37	0.789	0.0585	3.52	0.641	1.23	0.013	0.11	59.3	no
4	D15e	AZO/Ag15Cu85/AZO (segregated)	15/9/37	0.794	0.0564	3.31	0.643	1.23	0.019	0.16	59.3	no
5	M5	AZO/Ag25Cu75/AZO	35/10/35	0.784	0.0780	5.92	0.612	1.28	0.034	0.28	58.2	no
6	M3ema	AZO/Ag70Cu30/AZO (segregated)	35/10/35	0.840	0.0462	2.63	0.635	1.32	0.081	0.66	57.9	yes
7	M35e	AZO/Ag60Cu40/AZO (segregated)	15/9/35	0.843	0.0514	2.95	0.659	1.28	0.065	0.53	57.4	yes
8	S10	ITO/Ag70Cu30/ITO	35/10/35	0.848	0.0764	5.48	0.619	1.37	0.081	0.66	57.3	no
9	D10	AZO/Ag10Cu90/AZO	15/9/37	0.786	0.0784	5.66	0.638	1.23	0.013	0.11	57.1	no
10	D15	AZO/Ag15Cu85/AZO	15/9/37	0.790	0.0828	6.15	0.639	1.24	0.019	0.16	56.3	no
—	M0	AZO/Ag/AZO (benchmark)	35/10/35	0.876	0.0603	4.18	0.646	1.35	0.105	0.85	53.0	yes

Every entry uses a conductive oxide as the underlayer (AZO or ITO), for the reason in \$5.3 — the free carriers reject solar near-infrared, which a passive nitride cannot. Only **2 of ten meet the full specification**, and those use substantial silver. The rest fail on visible transmittance.

The AZO/Cu/Si₃N₄ hybrid (H2) now ranks **second** on this profile, which was not the case before the \$5.2 correction: it keeps AZO's solar-NIR rejection underneath while gaining five points of transmittance from the nitride overlayer, and remains silver-free.

This is the honest state of the cooling-climate answer: the framework is ranking near-misses. No single-metal architecture in the set clears T_{vis} ≥ 0.80 at acceptable solar gain, which is the finding that motivated the multi-layer work in \$5.4. The double-copper Si₃N₄ stack scores 68.9 on this profile — higher than anything in the table above — but at T_{vis} 0.716 it too falls short.

How to read these tables

1. **They share one candidate out of ten.** A recommendation is only meaningful with its climate profile named. Circulating one table without the other would be misleading — except for H2, which is defensible under either.
2. **The benchmark appears in neither top ten**, which is the correct answer to the brief's question: pure silver is the incumbent to beat, and on a sustainability-weighted objective it is beaten.
3. **Four of ten in each list are "segregated" variants** — the same composition under the alternative microstructure hypothesis. Until the Phase 2 measurement (\$8.3) is made, those four entries are conditional. \$5.5 provides thermodynamic support for segregation but not proof of the as-deposited state.
4. **All copper-bearing entries are contingent on \$6.** The framework under-predicts sputtered copper sheet resistance by

roughly eightfold; if that gap is real film quality rather than model error, most of both tables is affected.

5. **Scores are not comparable between the two tables**, being computed under different weightings. Compare within a column only.

5.7 The dilute-titanium ternary is predicted to underperform

Ag₇₀Cu₂₉Ti₁, proposed in the brief on the hypothesis that dilute Ti stabilises the metal layer, ranks 13th of 14 in the original candidate set. Titanium's bulk resistivity is 42 μΩ·cm, approximately 26× silver's; even at 1 at.% this raises alloy resistivity enough to give the worst sheet resistance (7.55 Ω/sq) and worst emissivity (0.0921) in the set. The interfacial benefit may be real, but the conductivity penalty is weighting-independent.

A titanium *barrier layer* remains the better test of the interface hypothesis, isolating the interfacial effect without placing Ti in the conduction path — as industrial coatings do. It is not, however, a silver-reduction candidate: it uses a full pure-silver layer and ranks last once silver consumption is weighted. The two claims should be kept separate.

6. The critical unknown, and the experiment that resolves it

6.1 The discrepancy

Validation against literature shows the model reproducing silver stacks well in the infrared — its intended strength — and failing on copper:

Benchmark	Metric	Reported	Modelled	Error
AZO/Ag(13)/AZO	Far-IR reflectance	0.960	0.964	0.4%
AZO/Cu/AZO (2022)	Sheet resistance	9.96	2.86	71%
AZO/Cu(15)/AZO	Sheet resistance	16.6	2.10	87%

The model under-predicts sputtered copper sheet resistance by approximately eightfold. The classical size effect cannot account for a gap of this magnitude, which points to a mechanism the model does not contain: oxygen incorporation during deposition, native oxide at the interfaces, or substantially poorer grain structure than silver on the same underlayer.

If this reading is correct, the obstacle to the copper route is film quality rather than intrinsic physics — an engineering problem with known levers (base pressure, seed layers, getter, substrate temperature) rather than a fundamental limit. That is a considerably more tractable target than replacing silver's electronic structure.

It also gates six of the leading candidates in both climate profiles.

A literature review has since narrowed the cause without any deposition. Fuchs-Sondheimer specularity and Mayadas-Shatzkes grain-boundary reflection are well characterised for copper because interconnect scaling depends on them. Four independent published fits give p between 0.48 and 0.80 and R between 0.16 and 0.43; the framework's assumed p = 0.50, R = 0.25 sits inside that range.

p	R	Source	Predicted R _s , AZO/Cu(15)/AZO
0.52	0.43	Chawla & Gall, <i>Phys. Rev. B</i> 81 , 155454 (2010)	2.69
0.48	0.27	twin-boundary study, nanocrystalline Cu	2.23
0.80	0.38	<i>Thin Solid Films</i> (2006)	2.17
≈0	0.17	<i>AIP Advances</i> 9 , 025015 (2019)	2.71
0.50	0.25	framework default	2.16

All cluster near 2.2-2.7 Ω/sq against the 16.6 to be explained. An exhaustive scan over the entire admissible range — p ∈ [0, 1], R ∈ [0, 0.6] — reaches only **4.42 Ω/sq**, short by a factor of 3.8.

No scattering parameters anywhere in the literature range explain the discrepancy. Decision rule A below is eliminated on that basis.

What does explain it is grain size. Both models take grain size as an input, and the framework assumes lateral grains three times the film thickness, appropriate to a coalesced film. Grains at roughly half the thickness give 14.1 Ω/sq:

Grain size	R _s (15 nm)
3.0 × thickness (assumed)	4.42
1.0 × thickness	8.31
0.5 × thickness	14.13
0.25 × thickness	25.77

That is a nanocrystalline structure — grains of order 5–8 nm in a 15 nm film — which is plausible for copper sputtered at room temperature onto an oxide it wets poorly. It is now the leading hypothesis, displacing oxygen contamination.

Caveat on transferability. The published values are for copper on Ta or SiO₂ at 25–158 nm, deposited for interconnects. This work concerns copper on AZO at 10–15 nm, where nucleation differs and the thickness lies below anything in the cited studies. The transferable conclusion is therefore the *negative* one — that p and R cannot account for the gap — rather than a positive calibration. Grain size for copper on AZO at these thicknesses was not found in the literature searched, and is the missing number. Full analysis in [docs/LITERATURE_CALIBRATION.md](#).

6.2 The experiment

Specified in [experiments/BENCH_cu_series.md](#) with pre-registered decision rules in [experiments/PROTOCOL_cu_series.md](#).

Matrix. Cu at 8, 10, 12, 14, 16, 18, 20 nm plus a 10 nm Ag control, all as AZO(40)/metal/AZO(40) capped trilayers, deposition order randomised. Plus one uncapped Cu film at 12 nm as an oxidation control.

Key design decisions.

Films must be capped. Bare 10 nm copper oxidises in air within minutes, and the hypothesis under test is that oxygen degrades these films. A bare film measured after venting reports air oxidation rather than deposition quality. The framework de-embeds the AZO shunt to recover the metal layer; the correction is non-linear and largest where it matters — a measured 16.6 Ω/sq trilayer is 22.6 Ω/sq in the metal alone, a 36% difference. Omitting it would bias the result toward "the copper is acceptable".

Order randomised. Target erosion drifts across a campaign; in ascending thickness order that drift aliases directly onto thickness and cannot be separated from a size effect.

Thickness measured independently. $\rho = R_s \cdot t$, so a 20% thickness error becomes a 20% resistivity error and would be misattributed to a scattering parameter.

Silver control is a stop condition. AZO/Ag(10)/AZO should give approximately 4–5 Ω/sq. If it does not, the tool requires diagnosis before the copper series can be interpreted.

A cheaper measurement now comes first. Because the leading hypothesis is grain structure, a **single XRD scan on one 12–15 nm copper film on AZO** gives the grain size directly by Scherrer broadening of the Cu(111) reflection, and discriminates between the remaining hypotheses:

- Grain size $\leq 0.6 \times$ film thickness → nanocrystalline structure confirmed; the model's grain assumption is wrong and the remedy is thermal or morphological (seed layer, elevated substrate temperature, brief anneal).
- Grain size $\geq$ film thickness → grain structure is not the cause, and attention returns to impurity scattering.

One sample rather than eight, and XRD is more widely available than a dedicated sputter session. **If only one measurement can be obtained, this is now the one to take.** The thickness series remains the better experiment where both are possible, since it also calibrates the model.

Analysis. One command:

```
pvdlowe calibrate -i experiments/cu_series_runsheet.csv --capped
```

This fits specularity, grain-boundary reflection, percolation threshold and a thickness-independent excess resistivity, then diagnoses which of three mechanisms is operating.

6.3 Pre-registered decision rules

Written before any data exists, so that interpretation is not selected to suit the outcome. Rule A was subsequently eliminated and rule E added by the literature review in §6.1, which was also completed before any deposition; both changes are recorded rather than applied silently.

Distinguishing E from B requires measuring grain size, not inferring it: a small-grain film and a contaminated film produce similar R_s(d) curves, so a thickness series alone cannot separate them.

Rule	Criterion	Interpretation	Consequence
A	Excess < 1 μΩ-cm, ρ(100 nm)/ρ_bulk < 1.5	Classical size effect; model form correct, parameters wrong	Eliminated by literature review (§6.1). Retained here unaltered so the amendment is auditable
E	XRD grain size $\leq 0.6 \times$ film thickness	Nanocrystalline grain structure — now the leading hypothesis	Set grain_size_ratio from the measured value and re-run the ranking. Remedy is thermal or morphological, not vacuum hygiene
B	Excess > 50% of bulk, improving fit by > 20%	Impurity scattering, most likely oxygen	Favourable: film quality, not physics. Follow with base-pressure study and XPS depth profile
C	Fitted d _c differs from 11 nm by > 1.5 nm	Dewetting on this underlayer	Minimum usable thickness changes, and with it every silver-consumption figure. Trial a seed layer
D	R _s at 15 nm near 16.6 Ω/sq	Literature is correct; model optics optimistic by ~8×	Six leading candidates fall. Programme reverts to silver reduction, with \$5.1's dilute-silver optimum as the recommendation in its own right

6.4 Validation of the analysis path

The fitter was tested against synthetic data generated with known parameters. All four cases were diagnosed correctly at 0.5–2.4% relative residual, and the percolation threshold was recovered to better than 1 nm in every case.

A limitation identified by that testing and stated in the protocol: specularity and grain-boundary reflection are **not separately identifiable** from $R_s(d)$ alone — across an 8–20 nm window they produce nearly the same $1/d$ dependence. A synthetic film generated with $p = 0.35$ was fitted at $p = 1.00$ with a 1.5% residual: an excellent fit to the data and an incorrect value for the parameter.

The fitted model therefore predicts sheet resistance reliably within the fitted range, which is what the framework requires, but the individual parameters must not be reported as measurements. Separating them requires varying grain size independently, for instance by annealing at fixed thickness. The percolation threshold **is** identifiable, and is the parameter of greatest consequence since it sets minimum usable thickness.

7. Limitations

7.1 No experimental validation

No films were deposited. Every performance figure in this report is a model output. The candidate rankings are hypotheses ordered by physics, suitable for directing experimental effort, and are not results.

7.2 Calibrated and fitted parameters

Parameter	Basis
Glass far-IR oscillator scale	Calibrated to bare-glass $\epsilon_n = 0.837$
TCO band-edge strength	Calibrated to $n(550\text{ nm})$
Ag percolation $d_c = 10\text{ nm}$	Literature, XRD-confirmed
Cu percolation $d_c = 11\text{ nm}$	Literature, unconfirmed
Drude damping	Anchored to DC resistivity
Specularity, grain-boundary reflection	Fitted, not measured

7.3 Known weaknesses

- Si₃N₄ and TiO₂ optical constants are ESTIMATE grade** — indices from typical sputtered values, phonon parameters order-of-magnitude.
- D65 and AM1.5 spectra are Planckian approximations**, flagged as MODEL. The cost of this has now been quantified rather than left open ([illuminant_sensitivity](#)): varying the assumed colour temperature over 5000–7500 K moves **T_{vis} by 0.1% and T_{sol} by 8.3%**. The asymmetry is structural — the photopic response $V(\lambda)$ is narrow and dominates the visible weighting, whereas in the solar band the spectrum *is* the weighting.

Consequence: T_{vis} is reportable as computed. **T_{sol}, and the g-value and LSG derived from it, carry a systematic uncertainty of order 5–10%** until a tabulated AM1.5G spectrum is supplied. Rankings within a climate profile are unaffected, the bias being common to all candidates, but absolute solar-gain figures quoted against a building code are. - **Visible-range metal optics are accurate to a few per cent at best.** The far-infrared response is reliable, being pure Drude and anchored to resistivity; the visible is not. - **Roughness, interdiffusion and barrier absorption are not modelled.** A real stack will transmit somewhat less than predicted. - **Reactive Si₃N₄ deposition is more demanding than AZO** — target poisoning, lower rate. The brief's \$15 deposition-efficiency criterion would penalise it, and the framework cannot score this without a calibrated rate model.

7.4 Scores are not portable between weightings

Absolute scores moved by approximately 25 points as the \$3 corrections were applied. **A score is not a property of a material.** A figure of 89.3 is a statement about one architecture under one weighting of eight criteria, three of which the framework cannot populate. Rankings should be quoted with the weighting file attached and the unverified elements identified.

8. Recommendations

8.1 Immediate — literature

- Obtain the full text of *Applied Surface Science* 578 (2022) 152051** and establish whether the reported emissivity is normal or hemispherical, and the instrument's spectral band. \$16's conclusion depends on this.

2. **Withdraw the two disputed citations** (§4.1) from any document derived from the brief pending identification of their source.
3. **Apply the three factual corrections** in §4.4.

8.2 First experimental priority

One XRD scan on a single 12-15 nm copper film on AZO. An afternoon, one sample. Following the literature review in §6.1, grain structure is the leading explanation for the model's largest error, and Scherrer broadening measures it directly. This is now the highest information-per-hour measurement available.

Then the copper thickness series (§6.2). Half a day of tool time. It confirms or refutes six leading candidates and calibrates the transport model. The protocol is written for handover and requires no further specification.

If both can be obtained, run both — the XRD identifies the mechanism, the series calibrates the model. If only one, take the XRD.

8.3 Second experimental priority

One AZO/Ag₇₀Cu₃₀/AZO film at 10 nm, sheet resistance measured. The two microstructure hypotheses predict 6.4 versus 2.6 Ω/sq — far outside probe resolution. Better still, measure across Ag 0, 25, 50, 75 at.%; the *curve shape* is diagnostic, with the segregated model predicting a flat $\sim 3 \Omega/\text{sq}$ and a metastable solid solution predicting a Nordheim maximum above 7 Ω/sq .

8.4 First deposition run for the target application

For a cooling-dominated application (Indian architectural glazing): **AZO/Cu/AZO at 45/12/45 nm**, measured for T_{vis} , sheet resistance and FTIR emissivity, against an AZO/Ag/AZO control.

For a heating-dominated application: **Si₃N₄/Cu/Si₃N₄ at 60/12/50 nm** against the same control.

Either comparison tests the dielectric hypothesis, the copper film-quality question and the silver-free premise simultaneously.

8.5 Framework extensions worth the effort

- **Finer optimisation of the double-copper stack** — asymmetric outer layers, mixed-metal pairing, finer dielectric steps. The transmittance deficit is 8 points and the scan performed was coarse. This is the most likely route to closing it, now that the triple-layer route has been ruled out (§5.4).
- **A tabulated AM1.5G spectrum**, to remove the 5-10% systematic on T_{sol} , g and LSG.
- **Measured n and k** for in-house AZO, Si₃N₄ and metal films — the largest single source of visible-range error.

9. Handover

Item	Location
Source, documentation, results	github.com/VarunMandy/pvdlowe
Archive	gs://sg-llamole-pvdlowe/pvdlowe/source/
Executive summary	docs/SUMMARY.md
Full findings	docs/FINDINGS.md
Physics and approximations	docs/METHODOLOGY.md
Evidence grading	docs/PROVENANCE.md
Experimental programme	docs/ROADMAP.md
Bench procedure	experiments/BENCH_cu_series.md
Pre-registered decision rules	experiments/PROTOCOL_cu_series.md
Blank run sheet	experiments/cu_series_runsheet.csv
Worked example output	experiments/EXAMPLE_filled_runsheet.csv

Installation is `pip install -e .`; the test suite (92 tests, no external dependencies beyond numpy/scipy/pandas/pyyaml) runs with `python tests/run_tests.py` (92 tests) and should be run after any environment change, as it validates the physics rather than only the interfaces.

10. Conclusion

The framework delivered implements the brief's proposed workflow and, in doing so, identified several respects in which the brief's own assumptions do not survive quantitative examination: a weighting scheme that omitted the programme's primary

objective, two citations that could not be traced, a measurement inconsistent with a model-independent physical limit, and a material class and stack architecture excluded by the search framing but outperforming the proposed candidates.

The candidate rankings produced should be treated as hypotheses for experimental prioritisation. Their principal weakness is known, quantified, and addressed by a specified experiment with pre-registered decision rules — which is offered as the more useful deliverable. A model that identifies the measurement capable of falsifying it is more valuable to an experimental programme than one that does not.

The recommended next action is half a day of sputter tool time.