


ENSAIO: 00000211DATA: 29/05/2025HORA: 07:46:16

NORMA: INDENTAI%I%O  
Identifica%I%O:D33 27/5  
Cil%LULA DE CARGA: 500 kgf (1)PRI% CARGA: 5,00 N

TEMPERATURA: 25,00i%CTRABALHO REALIZADO: INDENTAI%I%O

UMIDADE RELATIVA: 50,00 %

Cliente:



Amostra No.	INDENTAI%I%O N	INDENTAI%I%O N	INDENTAI%I%O N	3i%NDICE DE CONFORTO	ALTURA REAL mm
1	159,36	196,13	364,07	2,28	52,55
2	156,91	192,46	356,72	2,27	47,97
3	170,39	208,39	387,36	2,27	50,25
Valor M%nimo	156,906	192,456	356,717	2,273	47,970
Valor M%ximo	170,391	208,391	387,363	2,285	52,550
V. M%dio	162,218	198,993	369,384	2,277	50,257
D. Padri%o	7,183	8,344	15,999	0,006	2,290
Mediana	159,358	196,133	364,072	2,273	50,250

Informa%I%es do Ensaio: