

## FALCON GRIP PRODUCT SPECIFICATIONS

|                              |  |
|------------------------------|--|
| <b>Name of Product</b>       | - 7 Mil Powder free Nitrile Gloves.            |
| <b>Name of Manufacturer</b>  | - Innovative Gloves Co. Ltd. Hatyai, Thailand. |
| <b>Base Material</b>         | - Nitrile.                                     |
| <b>Characteristics</b>       | - Non-Sterile, Ambidextrous Beaded Cuff.       |
| <b>Available Sizes</b>       | - Small, Medium, Large, X-Large, XX-Large.     |
| <b>Surface</b>               | - Diamond Textured.                            |
| <b>Surface Treatment</b>     | - Polymer Coating.                             |
| <b>Color</b>                 | - Orange.                                      |
| <b>Total Residue Content</b> | - < 2.0 Milligrams per glove.                  |



### Physical Specifications:

| Size     | Length(mm/inch) | Thickness(mm)<br>Single Wall |                      |                       |                     | Width(mm) |
|----------|-----------------|------------------------------|----------------------|-----------------------|---------------------|-----------|
|          |                 | Tip Smooth Surface           | Tip Textured Surface | Palm Textured Surface | Cuff Smooth Surface |           |
| Small    | 240±5           | 0.19±0.01                    | 0.28±0.01            | 0.23±0.01             | 0.11±0.01           | 85±5      |
| Medium   | 240±5           | 0.19±0.01                    | 0.28±0.01            | 0.23±0.01             | 0.11±0.01           | 95±5      |
| Large    | 240±5           | 0.19±0.01                    | 0.28±0.01            | 0.23±0.01             | 0.11±0.01           | 105±5     |
| X-Large  | 240±5           | 0.19±0.01                    | 0.28±0.01            | 0.23±0.01             | 0.11±0.01           | 115±5     |
| XX-Large | 240±5           | 0.19±0.01                    | 0.28±0.01            | 0.23±0.01             | 0.11±0.01           | 120±3     |

## Tensile (ASTM D412 & EN 455-2)

### Before Aging

| Tensile(MPA) | Elongation(%) | Force At Break(N) |
|--------------|---------------|-------------------|
| 22 Mpa Min.  | 500 Min.      | ≥ 6 N             |

### After Accelerated Aging

| Tensile(MPA) | Elongation(%) | Force At Break(N) |
|--------------|---------------|-------------------|
| 22 Mpa Min.  | 400 Min.      | ≥ 6 N             |

## Packaging

|                                       |  |
|---------------------------------------|--|
| <b>Packaging (Normal)</b>             | 100±2 pieces in one Dispenser Box, 10 Dispenser Box in one Carton. |
| <b>Labeling on Dispenser (Normal)</b> | Product Name, Size, Lot no. Quantity, Manufacturer's address.      |
| <b>Labeling on Carton (Normal)</b>    | Product Name, Size, Lot no. Quantity, Country of Origin.           |

## Container Loadability (No MOQ in manufacturer owned brand in standard Packaging)

20 FCL=780 Cartons.

40 FCL=1580 Cartons.

## Certification

