

## SILVER LINE PRODUCT SPECIFICATIONS

|  |   |  |
|--|---|--|
| <b>Name of Product</b>                   | - | 14 Mil Powder free Latex House Hold Gloves.                |
| <b>Name of Manufacturer</b>              | - | Innovative Gloves Co. Ltd. Hatyai, Thailand.               |
| <b>Base Material</b>                     | - | Natural Rubber Latex.                                      |
| <b>Characteristics</b>                   | - | Non-Sterile, Ambidextrous Beaded Cuff.                     |
| <b>Available Sizes</b>                   | - | Small, Medium, Large, X-Large, XX-Large.                   |
| <b>Surface</b>                           | - | Diamond Textured.  |
| <b>Surface Treatment</b>                 | - | Mild Washing with Chlorine Solution and Extensive Washing. |
| <b>Color</b>                             | - | White/Blue.  |
| <b>Total Residue Content</b>             | - | < 2.0 Milligrams per glove.                                |
| <b>Total Extractable protein content</b> | - | < 50 $\mu$ gram/ gram of glove                             |



### Physical Specifications:

| Size         | Length(mm/inch) | Thickness(mm)<br>Single Wall |                      |                       |                     | Width(mm)   |
|--------------|-----------------|------------------------------|----------------------|-----------------------|---------------------|-------------|
|              |                 | Tip Smooth Surface           | Tip Textured Surface | Palm Textured Surface | Cuff Smooth Surface |             |
| Small(7)     | 300 $\pm$ 10    | 0.37 $\pm$ 0.01              | 0.66 $\pm$ 0.02      | 0.74 $\pm$ 0.02       | 0.21 $\pm$ 0.01     | 95 $\pm$ 5  |
| Medium(8)    | 300 $\pm$ 10    | 0.37 $\pm$ 0.01              | 0.66 $\pm$ 0.02      | 0.74 $\pm$ 0.02       | 0.21 $\pm$ 0.01     | 100 $\pm$ 5 |
| Large(9)     | 300 $\pm$ 10    | 0.37 $\pm$ 0.01              | 0.66 $\pm$ 0.02      | 0.74 $\pm$ 0.02       | 0.21 $\pm$ 0.01     | 115 $\pm$ 5 |
| X-Large(10)  | 300 $\pm$ 10    | 0.37 $\pm$ 0.01              | 0.66 $\pm$ 0.02      | 0.74 $\pm$ 0.02       | 0.21 $\pm$ 0.01     | 120 $\pm$ 3 |
| XX-Large(11) | 300 $\pm$ 10    | 0.37 $\pm$ 0.01              | 0.66 $\pm$ 0.02      | 0.74 $\pm$ 0.02       | 0.21 $\pm$ 0.01     | 125 $\pm$ 3 |

## Tensile (ASTM D412 & EN 455-2)

### Before Aging

| Tensile(MPA) | Elongation(%) | Force At Break(N) |
|--------------|---------------|-------------------|
| 21 Mpa Min.  | 700 Min.      | ≥ 6 N             |

### After Accelerated Aging

| Tensile(MPA) | Elongation(%) | Force At Break(N) |
|--------------|---------------|-------------------|
| 18 Mpa Min.  | 500 Min.      | ≥ 6 N             |

## Packaging

|                                       |  |
|---------------------------------------|--|
| <b>Packaging (Normal)</b>             | 50±1 pieces in one Dispenser Box or Poly Bag, 10 Dispenser Box or Poly Bag in one Carton.  |
| <b>Labeling on Dispenser (Normal)</b> | Product Name, Size, Lot no. Quantity, Manufacturer's address, Warning about Latex Allergy. |
| <b>Labeling on Carton (Normal)</b>    | Product Name, Size, Lot no. Quantity, Country of Origin.                                   |

## Container Loadability (No MOQ in manufacturer owned brand in standard Packaging)

20 FCL=627 Cartons.

40 FCL=1260 Cartons.

## Certification

