

BLACK BARRIER PRODUCT SPECIFICATIONS

| | |
|------------------------------|---|
| Name of Product | - 5 Mil Powder free Nitrile Exam Gloves. |
| Name of Manufacturer | - Innovative Gloves Co. Ltd. Hatyai, Thailand. |
| Base Material | - Nitrile. |
| Characteristics | - Non-Sterile, Powder free, Ambidextrous Beaded Cuff. |
| Available Sizes | - X-Small, Small, Medium, Large, X-Large, XX-Large. |
| Surface | - Textured. |
| Surface Treatment | - Polymer Coated. |
| Colour | - Black. |
| Total Residue Content | - < 2.0 Milligrams per glove. |



Physical Specifications:

| Size | Length(mm/inch) | Thickness(mm) Single Wall | | | Width(mm) |
|----------|-----------------|------------------------------|-----------|-----------|-----------|
| | | Tip | Palm | Cuff | |
| X-Small | 240±5 | 0.14±0.01 | 0.11±0.01 | 0.09±0.01 | 75±5 |
| Small | 240±5 | 0.14±0.01 | 0.11±0.01 | 0.09±0.01 | 85±5 |
| Medium | 240±5 | 0.14±0.01 | 0.11±0.01 | 0.09±0.01 | 95±5 |
| Large | 240±5 | 0.14±0.01 | 0.11±0.01 | 0.09±0.01 | 105±5 |
| X-Large | 240±5 | 0.14±0.01 | 0.11±0.01 | 0.09±0.01 | 115±5 |
| XX-Large | 240±5 | 0.14±0.01 | 0.11±0.01 | 0.09±0.01 | 120±3 |

Tensile (D412 & EN 455-2)

Before Aging

| Tensile(MPA) | Elongation(%) | Force At Break(N) |
|--------------|---------------|-------------------|
| 22 Mpa Min. | 500 Min. | ≥ 6 N |

After Accelerated Aging

| Tensile(MPA) | Elongation(%) | Force At Break(N) |
|--------------|---------------|-------------------|
| 22 Mpa Min. | 400 Min. | ≥ 6 N |

Packaging

| | |
|---------------------------------------|--|
| Packaging (Normal) | 100±1 pieces in one Dispenser Box, 10 Dispenser Box in one Carton, 1000 Gloves Per Carton. |
| Labeling on Dispenser (Normal) | Product Name, Size, Lot no. Quantity, Manufacturer's address, Warning about Latex Allergy. |
| Labeling on Carton (Normal) | Product Name, Size, Lot no. Quantity, Country of Origin. |

Container Loadability (No MOQ in manufacturer owned brand in standard Packaging)

20 FCL=1360 Cartons.

40 FCL=2740 Cartons.

Certification

