



Standard Specification for Carbon Structural Steel¹

This standard is issued under the fixed designation A 36/A 36M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This specification² covers carbon steel shapes, plates, and bars of structural quality for use in riveted, bolted, or welded construction of bridges and buildings, and for general structural purposes.

1.2 Supplementary requirements are provided for use where additional testing or additional restrictions are required by the purchaser. Such requirements apply only when specified in the purchase order.

1.3 When the steel is to be welded, a welding procedure suitable for the grade of steel and intended use or service is to be utilized. See Appendix X3 of Specification A 6/A 6M for information on weldability.

1.4 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system is to be used independently of the other, without combining values in any way.

1.5 The text of this specification contains notes or footnotes, or both, that provide explanatory material. Such notes and footnotes, excluding those in tables and figures, do not contain any mandatory requirements.

1.6 For structural products produced from coil and furnished without heat treatment or with stress relieving only, the additional requirements, including additional testing requirements and the reporting of additional test results, of A 6/A 6M apply.

2. Referenced Documents

2.1 ASTM Standards:³

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel, and Related Alloys, and is the direct responsibility of Subcommittee A01.02 on Structural Steel for Bridges, Buildings, Rolling Stock, and Ships.

Current edition approved March 1, 2005. Published March 2005. Originally approved in 1960. Last previous edition approved in 2004 as A 36/A 36M – 04.

² For ASME Boiler and Pressure Vessel Code Applications, see related Specifications SA-36 in Section II of that Code.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

A 6/A 6M Specification for General Requirements for Rolled Structural Steel Bars, Plates, Shapes, and Sheet Piling

A 27/A 27M Specification for Steel Castings, Carbon, for General Application

A 307 Specification for Carbon Steel Bolts and Studs, 60 000 psi Tensile Strength

A 325 Specification for Structural Bolts, Steel, Heat Treated, 120/105 ksi Minimum Tensile Strength

A 325M Specification for Structural Bolts, Steel, Heat Treated 830 MPa Minimum Tensile Strength [Metric]

A 500 Specification for Cold-Formed Welded and Seamless Carbon Steel Structural Tubing in Rounds and Shapes

A 501 Specification for Hot-Formed Welded and Seamless Carbon Steel Structural Tubing

A 502 Specification for Rivets, Steel, Structural

A 563 Specification for Carbon and Alloy Steel Nuts

A 563M Specification for Carbon and Alloy Steel Nuts [Metric]

A 1011/A 1011M Specification for Steel, Sheet and Strip, Hot-Rolled, Carbon, Structural High Strength Low Alloy, and High Strength Low Alloy with Improved Formability

A 668/A 668M Specification for Steel Forgings, Carbon and Alloy, for General Industrial Use

F 568M Specification for Carbon and Alloy Steel Externally Threaded Metric Fasteners

3. Appurtenant Materials

3.1 When components of a steel structure are identified with this ASTM designation but the product form is not listed in the scope of this specification, the material shall conform to one of the standards listed in **Table 1** unless otherwise specified by the purchaser.

4. General Requirements for Delivery

4.1 Structural products furnished under this specification shall conform to the requirements of the current edition of Specification A 6/A 6M, for the specific structural product ordered, unless a conflict exists in which case this specification shall prevail.

*A Summary of Changes section appears at the end of this standard.

TABLE 1 Appurtenant Material Specifications

NOTE 1—The specifier should be satisfied of the suitability of these materials for the intended application. Chemical composition and/or mechanical properties may be different than specified in A 36/A 36M.

Material	ASTM Designation
Steel rivets	A 502, Grade 1
Bolts	A 307, Grade A or F 568M, Class 4.6
High-strength bolts	A 325 or A 325M
Steel nuts	A 563 or A 563M
Cast steel	A 27/A 27M, Grade 65–35 [450–240]
Forgings (carbon steel)	A 668, Class D
Hot-rolled sheets and strip	A 1011/A 1011M, SS Grade 36[250] Type 1 or Type 2 or A 1018/A 1018M SS Grade 36[250]
Cold-formed tubing	A 500, Grade B
Hot-formed tubing	A 501
Anchor bolts	F 1554

4.2 Coils are excluded from qualification to this specification until they are processed into a finished structural product. Structural products produced from coil means structural products that have been cut to individual lengths from a coil. The processor directly controls, or is responsible for, the operations involved in the processing of a coil into a finished structural product. Such operations include decoiling, leveling or straightening, hot-forming or cold-forming (if applicable), cutting to length, testing, inspection, conditioning, heat treatment (if applicable), packaging, marking, loading for shipment, and certification.

NOTE 1—For structural products produced from coil and furnished without heat treatment or with stress relieving only, two test results are to be reported for each qualifying coil. Additional requirements regarding structural products produced from coil are described in Specification A 6/A 6M.

5. Bearing Plates

5.1 Unless otherwise specified, plates used as bearing plates for bridges shall be subjected to mechanical tests and shall conform to the tensile requirements of Section 8.

5.2 Unless otherwise specified, mechanical tests shall not be required for plates over 1½ in. [40 mm] in thickness used as bearing plates in structures other than bridges, subject to the requirement that they shall contain 0.20 to 0.33 % carbon by heat analysis, that the chemical composition shall conform to the requirements of Table 2 in phosphorus and sulfur content, and that a sufficient discard shall be made to secure sound plates.

6. Materials and Manufacture

6.1 The steel for plates and bars over ½ in. [12.5 mm] in thickness and shapes with flange or leg thicknesses over 1 in. [25 mm] shall be semi-killed or killed.

7. Chemical Composition

7.1 The heat analysis shall conform to the requirements prescribed in Table 2, except as specified in 5.2.

7.2 The steel shall conform on product analysis to the requirements prescribed in Table 2, subject to the product analysis tolerances in Specification A 6/A 6M.

8. Tension Test

8.1 The material as represented by the test specimen, except as specified in 5.2 and 8.2, shall conform to the requirements as to the tensile properties prescribed in Table 3.

8.2 Shapes less than 1 in.² [645 mm²] in cross section and bars, other than flats, less than ½ in. [12.5 mm] in thickness or diameter need not be subjected to tension tests by the manufacturer, provided that the chemical composition used is appropriate for obtaining the tensile properties in Table 3.

9. Keywords

9.1 bars; bolted construction; bridges; buildings; carbon; plates; riveted construction; shapes; steel; structural steel; welded construction

TABLE 2 Chemical Requirements

NOTE 1—Where “...” appears in this table, there is no requirement. The heat analysis for manganese shall be determined and reported as described in the heat analysis section of Specification A 6/A 6M.

Product	Shapes ^A	Plates ^B					Bars ^B			
		To ¾ to 1½ [20], incl	Over ¾ to 1½ [20 to 40], incl	Over 1½ to 2½ [40 to 65], incl	Over 2½ to 4 [65 to 100], incl	Over 4 [100]	To ¾ to 1½ [20], incl	Over ¾ to 1½ [20 to 40], incl	Over 1½ to 4 [100], incl	Over 4 [100]
Thickness, in. [mm]	All									
Carbon, max, %	0.26	0.25	0.25	0.26	0.27	0.29	0.26	0.27	0.28	0.29
Manganese, %	0.80–1.20	0.80–1.20	0.85–1.20	0.85–1.20	...	0.60–0.90	0.60–0.90	0.60–0.90
Phosphorus, max, %	0.04	0.04	0.04	0.04	0.04	0.04	0.04	0.04	0.04	0.04
Sulfur, max, %	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05	0.05
Silicon, %	0.40 max	0.40 max	0.40 max	0.15–0.40	0.15–0.40	0.15–0.40	0.40 max	0.40 max	0.40 max	0.40 max
Copper, min, % when cop- per steel is specified	0.20	0.20	0.20	0.20	0.20	0.20	0.20	0.20	0.20	0.20

^AManganese content of 0.85–1.35 % and silicon content of 0.15–0.40 % is required for shapes with flange thickness over 3 in. [75 mm].

^BFor each reduction of 0.01 percentage point below the specified carbon maximum, an increase of 0.06 percentage point manganese above the specified maximum will be permitted, up to the maximum of 1.35 %.

**TABLE 3 Tensile Requirements^A**

Plates, Shapes, ^B and Bars:	
Tensile strength, ksi [MPa]	58–80 [400–550]
Yield point, min, ksi [MPa]	36 [250] ^C
Plates and Bars ^{D,E} :	
Elongation in 8 in. [200 mm], min, %	20
Elongation in 2 in. [50 mm], min, %	23
Shapes:	
Elongation in 8 in. [200 mm], min, %	20
Elongation in 2 in. [50 mm], min, %	21 ^B

^ASee the Orientation subsection in the Tension Tests section of Specification A 6/A 6M.

^BFor wide flange shapes with flange thickness over 3 in. [75 mm], the 80 ksi [550 MPa] maximum tensile strength does not apply and a minimum elongation in 2 in. [50 mm] of 19 % applies.

^CYield point 32 ksi [220 MPa] for plates over 8 in. [200 mm] in thickness.

^DElongation not required to be determined for floor plate.

^EFor plates wider than 24 in. [600 mm], the elongation requirement is reduced two percentage points. See the Elongation Requirement Adjustments subsection under the Tension Tests section of Specification A 6/A 6M.

SUPPLEMENTARY REQUIREMENTS

These requirements shall not apply unless specified in the order.

Standardized supplementary requirements for use at the option of the purchaser are listed in Specification A 6/A 6M. Those that are considered suitable for use with this specification are listed by title:

S5. Charpy V-Notch Impact Test.

S30. Charpy V-Notch Impact Test for Structural Shapes: Alternate Core Location

S32. Single Heat Bundles

S32.1 Bundles containing shapes or bars shall be from a single heat of steel.

In addition, the following optional supplementary requirement is also suitable for use with this specification:

S97. Limitation on Rimmed or Capped Steel

S97.1 The steel shall be other than rimmed or capped.

SUMMARY OF CHANGES

Committee A01 has identified the location of the following changes to this standard since A 36/A 36M-03a that may impact the use of this standard. (Approved March 1, 2005.)

(1) Paragraph 6.1 was revised.

Committee A01 has identified the location of the following changes to this standard since A 36/A 36M-03a that may impact the use of this standard. (Approved April 1, 2004.)

(1) Table 2 has been revised to make Footnote B also apply to bars.

(2) Supplementary Requirement S32 was added.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).

ASTM International
100 Barr Harbor Drive
West Conshohocken, PA 19428-2959
U.S.A.
Tel: 610-832-9585
Fax: 610-832-9555
E-mail: service@astm.org
Web: www.astm.org