

Riccardo Campigotto

Da: Miguel Blanes <blanes.miguel@gmail.com>
Inviato: lunedì 19 luglio 2021 11:37
A: Roberto Berti
Cc: Riccardo Campigotto
Oggetto: Re: I: Ackerstein's Roof Tiles

Hi Roberto,

In relation to the differences that I identify in the tiles in the photos, I consider that there may be several possibilities or some that are the sum of them that can give this result, I do not indicate anything about the extrusion conditions "extrusión head", without first knowing the basis of the raw materials and their mixture in the concrete mixer:

1) The GRANULOMETRY of the sand, normally it is indicated from 0 to 5 mm, but the percentage of sand grains of 4.76 mm is almost 0 %, (since in the areas of the minimum thickness of the tile that grain size is of no interest) so from 3/ 3.5 mm is the largest working grain and with a maximum percentage of 15%.
(It would be necessary to know the granulometric curve of the sand to evaluate).

2) The TYPE OF SAND is another important part, if the origin of the sand is from the river and with rounded faces it is the best, it can be from a mine, on the other hand, crushed sand is the worst to work with.
(It would be necessary to find out where the sand used comes from)

3) The good MIXTURE in the concrete mixer, the mixture times in dry and wet must be the best to mix the materials well, so that there is a good cohesion of all the raw materials.
(It is necessary to know the raw materials used and the mixture times for each of them)

4) Excess WATER can cause voids in the concrete during extrusion, which can be identified in the cut.
(The working moisture of the concrete should be known)

I remain open to any questions or comments.

Thank you.

Best Regards.