

REPORT ON THICKNESS AND WEIGHT MEASUREMENTS – DOUBLE ROMAN TILE 281125

Following a review of the measurements recorded for fresh tiles, the following assessments and control proposals are presented:

a) Initial Process Verification

It is agreed that multiple measurements will be taken at the start of production (09:00) to verify that thicknesses—including the Q2 measurement—and weight conform to established specifications.

b) Control Frequency and Material Management

Once the extrusion head is adjusted and stabilized, hourly controls will be implemented during production. Concrete discarded during these verifications can be recycled by reintroducing it into the extruder hopper.

c) Analysis of Discrepancies in Data from 261125

An inconsistency is observed in the variations of thickness and weight recorded between 07:55 and 09:00 hours—with an unexplained increase in both values—unless the height of the extrusion box was modified (a change that must be recorded in the production report) or a sudden variation in the concrete's humidity occurred.

7:55	26/11	7.8		12.9	11.5	12.2	10.1	4.34	96	83
8:30	26/11									
9:00	26/11	8.6		13	11.8	12.8	10.3	4.49	96	83
9:10	26/11	7.3		12.4	11	12	11.0	4.3	96	83
9:30	26/11	7.4		12.9	11	11.7	10.3	4.32	96	83

It is equally inconsistent that the roller consumption (96) and push chain (83) values remain unchanged with identical thickness and weight measurements. The cause of this discrepancy must be investigated.

d) Complementary Control on Cured Tiles

The control in the wet state must be complemented with:

*Verification of measurements on cured tiles, to confirm that dimensional patterns are maintained.

*Sample installation of 10 tiles, to validate the correct interlocking of the upper and lower profiles—an aspect that thickness measurements cannot verify.

e) Breakage Tests and Dispatch Criteria

Breakage tests on the machine are an essential indicator that must be monitored to evaluate product evolution and compare its performance before dispatch. Tiles destined for roof installation should preferably have

f) Roof Breakage Analysis

To accurately determine the origin of breakages on site, it is essential to characterize the type of tile fracture, its angle, and the crack's point of origin. Additionally, the thickness of the affected tiles must be measured and compared against reference values.