
## **McMASTER-CARR**<sub>®</sub>

## Clear Scratch- and UV-Resistant Cast Acrylic Sheet 12" x 24" x 1/8"

\$16.70 Each 8560K257





Clear

Material	Acrylic Plastic
Shape	Sheet and Bar
Texture	Smooth
Clarity	Clear
Light	92%
Transmission	
Thickness	1/8"
Thickness	-0.025" to 0.015"
Tolerance	
Tolerance	Standard
Rating	
Width	12"
Width Tolerance	-1/4" to 1/4"
Length	24"
Length	-1/4" to 1/4"
Tolerance	
Color	Clear
Backing Type	Plain
Hardness	Rockwell M94-M100
Hardness Rating	Hard
For Use	Yes
Outdoors	
Temperature	-40° to 170° F
Range	
Impact Strength	0.3-0.4 ftlbs./in.
Impact Strength	Poor
Rating	
Tensile Strength	10,000-11,250 psi
Tensile Strength	Good
Rating	
Chemical	
Resistance Excellent	Acatic Acid Diagol Eugl
Excellent	Acetic Acid, Diesel Fuel, Hydrochloric Acid, Kerosene,
	Mineral Oil, Phosphoric Acid, Sodium Hydroxide, Water
Moderate	Bleach, Chlorine, Coolant, Fuel Oil, Gasoline, Heating Oil,
	Isopropyl Alcohol
Not	Acetone, Hydrogen Peroxide,
Recommended	Lacquer Solvents, Methanol,

st Acrylic Sheet, 12" x 24"	x 1/8"   McMaster-Carr
	Methyl Ethyl Ketone (MEK), Nitric Acid, Sulfuric Acid
Not Rated	Hydraulic Fluid, Synthetic Oil, Vegetable Oil
Fabrication	Cast
Density	0.043 lbs./cu. in.
Flexural	450,000-470,000 psi
Modulus	
Flexibility	Semi-Rigid
Coefficient of	0.8
Friction	
Friction Rating	Not Slippery
Dielectric	400-500 V/mil
Strength	
Electrical	Good
Insulation Rating	
Water	0.2-0.33%
Absorption	0.2-0.00 /0
Water	
Absorption	Poor
Rating	
Coefficient of Thermal Expansion	3.4 to 4.2 × 10 <sup>-5</sup> in./in./°F
Thermal Stability	Good
Comparable To	Acrylite, Lucite, Perspex, Plexiglas® Acrylic, Polycast
Performance Properties	Clear, Easy to Thermoform, Electrical Insulator, Food Contact, High Strength, Low Thermal Expansion, Multipurpose, Weather Resistant
For Use With	Acetic Acid, Bleach, Chlorine, Coolant, Diesel Fuel, Fuel Oil, Gasoline, Heating Oil, Hydrochloric Acid, Isopropyl Alcohol, Kerosene, Mineral Oil, Phosphoric Acid, Sodium Hydroxide, Water
Specifications Met	Made of FDA Listed Material
Warning Message	Physical and mechanical properties are not guaranteed. They are intended only as a basis for comparison and not for design purposes.
RoHS	RoHS 3 (2015/863/EU)
	Compliant
REACH	REACH (EC 1907/2006) (01/16/2020, 205 SVHC) Compliant

Country of

Mexico

Origin

These cast acrylic sheets, bars, and cubes are often fabricated into tanks, see-through barrier panels, and light fixture lenses. Cast acrylic, which is comparable to Lucite and Plexiglas® Acrylic, is easier to machine than extruded acrylic. This material is scratch and UV resistant; it stands up to outdoor use better than polycarbonate and maintains clarity over time.