



Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	LOT NO(로트번호)	ISSUED DATE(발행일자)
세종에이앤에스	0.15*168	20250529 -01 ~ 02	2025-05-29
규격(재질)		LOT SIZE(수량)	
0.15*168 Cu	Ni 1.0~2.0μm	638.3 Kg	

I. VISUAL INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea)

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION
1	DISCOLORATION(변색)	0/1	OK	6	NO PLATING(미도금)
2	STAIN(얼룩)	0/1	OK	7	PEELING(도금 벗겨짐)
3	RUST(부식)	0/1	OK	8	LUMP(도금물침)
4	CONTAMINATION(오염)	0/1	OK	9	CAMBER(휨)
5	BENT(변형)	0/1	OK	10	PLATING BURR (도금)

II. DIMENSION INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/S

NO	항목/구분	SPEC			검사주기	우리하이피	
		규격	하한(-)	상한(+)		1차	2차
1	전폭	168.0	-0.1		Reel/Lot	167.998	
2							
3							
4							
5							
6							
7							
8							
9							
10							

III. PLATING THICKNESS(도금두께) (Sampling Plan : 1y

NO	SPECIFICATION	Measurement Data	RESULT
1	X-Ray 측정	첨부 : 도금성적서	OK
	Ni 1.0~2.0μm	첨부 : 도금성적서	

IV. FUNC

NO		RESULT
1		OK

제품도면		리하이피	김영란	조승현	종합판정	
		고객	작성	승인	종합판정	

업체명 : 세종에이앤에스

품명 : 0.15x168 초물 LOT NO : 250529-01 DATE : 25.05.29.

No	μm Ni	Ni	tolerance
		1.276	1.339 1.402
1	1.323		
2	1.402		
3	1.330		
4	1.304		
5	1.337		
Mean	1.339		
S.Dev	0.037		


FUNC: MEASURE
COL : 0.100 mm

$\frac{\text{Ni}}{\text{Cu}}$

SEC : 15 Sec

표준편차 0.037
변동계수 2.778

우리하이피



업체명 : 세종에이앤에스


품명 : 0.15x168 종물 LOT NO : 250529-01 DATE : 25.05.29.

No	μm Ni	Ni tolerance	
		1.318	1.345 1.372
1	1.338		
2	1.352		
3	1.372		
4	1.319		
5	1.345		
Mean	1.345		
S.Dev	0.019		

FUNC: MEASURE
COL : 0.100 mm

$\frac{\text{Ni}}{\text{Cu}}$

SEC : 15 Sec



도금원소 : Ni//Cu
측정값 개수 5
최대값 1.372
최소값 1.319
범위 0.053
평균값 1.345
표준편차 0.019
변동계수 1.441

우리하이피

