



Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	LOT NO(로트번호)	ISSUED DATE(발행일자)
세종에이앤에스	0.15*159	20250721 -01 ~ 02	2025-07-21
규격(재질)		LOT SIZE(수량)	
0.15*159 Cu	Ni 1.0~2.0μm	719 Kg	

I. VISUAL INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/5Reel)

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION
1	DISCOLORATION(변색)	0/1	OK	6	NO PLATING(미도금)
2	STAIN(얼룩)	0/1	OK	7	PEELING(도금 벗겨짐)
3	RUST(부식)	0/1	OK	8	LUMP(도금물짐)
4	CONTAMINATION(오염)	0/1	OK	9	CAMBER(휨)
5	BENT(변형)	0/1	OK	10	PLATING BURR (도금)

II. DIMENSION INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/5Reel)

NO	항목/구분	SPEC			검사주기	우리하이피	
		규격	하한(-)	상한(+)		1차	2차
1	전폭	159.0	-0.1		Reel/Lot	158.998	
2							
3							
4							
5							
6							
7							
8							
9							
10							

III. PLATING THICKNESS(도금두께) (Sampling Plan : 1y)

NO	SPECIFICATION	Measurement Data	RESULT
1	X-Ray 측정	첨부 : 도금성적서	OK
	Ni 1.0~2.0μm	첨부 : 도금성적서	


IV. FUNCTION

NO	RESULT
1	OK

제품도면		리하이피	김영란	조승현	합판정	
		고객	작성	승인	종합판정	

업체명 : 세종에이앤에스

품명 : 0.15x159 초물 LOT NO : 250721-01 DATE : 25.07.21.

No	μm Ni	Ni tolerance	
		1.237	1.321 1.405
1	1.253		
2	1.405		
3	1.402		
4	1.288		
5	1.257		
Mean	1.321		
S.Dev	0.077		


FUNC: MEASURE
COL : 0.100 mm

$\frac{\text{Ni}}{\text{Cu}}$

SEC : 15 Sec

표준편차 0.077
변동계수 5.793

우리하이피



업체명 : 세종에이앤에스


품명 : 0.15x159 종물 LOT NO : 250721-01 DATE : 25.07.21.

No	μm Ni	Ni tolerance
1	1.203	1.028 1.304 1.580
2	1.238	
3	1.245	
4	1.255	
5	1.580	
Mean	1.304	
S.Dev	0.155	

FUNC: MEASURE
COL : 0.100 mm


$\frac{\text{Ni}}{\text{Cu}}$

SEC : 15 Sec



도금원소 : Ni//Cu

측정값 개수 5
 최대값 1.580
 최소값 1.203
 범위 0.377
 평균값 1.304
 표준편차 0.155
 변동계수 11.916



우리하이피