



Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	LOT NO(로트번호)	ISSUED DATE(발행일자)
세종에이앤에스	0.15*175	20250818 -01~02	2025-08-18
규격(재질)		LOT SIZE(수량)	
0.15*175 Cu	Ni 1.0~2.0 μ m	876.2 Kg	

I. VISUAL INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/S)

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION
1	DISCOLORATION(변색)	0/1	OK	6	NO PLATING(미도금)
2	STAIN(얼룩)	0/1	OK	7	PEELING(도금 벗겨짐)
3	RUST(부식)	0/1	OK	8	LUMP(도금물침)
4	CONTAMINATION(오염)	0/1	OK	9	CAMBER(휨)
5	BENT(변형)	0/1	OK	10	PLATING BURR (도금)

II. DIMENSION INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/S)

NO	항목/구분	SPEC			검사주기	우리하이피	
		규격	하한(-)	상한(+)		1차	2차
1	전폭	175.0	-0.1		Reel/Lot	174.998	
2							
3							
4							
5							
6							
7							
8							
9							
10							

8/18
0.15 x 175
① 438.1
② 438.1
중 876.2kg

III. PLATING THICKNESS(도금두께) (Sampling Plan : 1y)

NO	SPECIFICATION	Measurement Data	RESULT
1	X-Ray 측정 Ni 1.0~2.0 μ m	첨부 : 도금성적서	OK
		첨부 : 도금성적서	

NO		RESULT
1		OK

제품도면	0.15*175 175.0	하이피	김영란	조승현	합판정	2025-08-18 우리하이피(주) Q.C
		고객	작성	승인	종합판정	

업체명 : 세종에이앤에스

품명 : 0.15x175 초물 LOT NO : 250818-01 DATE : 25.08.18.

No	μm Ni	Ni	tolerance
1	1.297	1.274	1.328
2	1.303		
3	1.322		
4	1.337		
5	1.383		
Mean	1.328		
S.Dev	0.034		


FUNC: MEASURE
COL : 0.100 mm

$\frac{\text{Ni}}{\text{Cu}}$

SEC : 15 Sec

평균값 1.328
표준편차 0.034
변동계수 2.588

우리하이피



업체명 : 세종에이앤에스


품명 : 0.15x175 종물 LOT NO : 250818-01 DATE : 25.08.18.

No	µm Ni	Ni tolerance 1.306 1.408 1.510
1	1.320	
2	1.385	
3	1.510	
4	1.428	
5	1.398	
Mean	1.408	
S.Dev	0.069	

FUNC: MEASURE
COL : 0.100 mm

$\frac{\text{Ni}}{\text{Cu}}$

SEC : 15 Sec



도금원소 : Ni//Cu
측정값 개수 5
최대값 1.510
최소값 1.320
범위 0.190
평균값 1.408
표준편차 0.069
변동계수 4.917

우리하이피

