



Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	LOT NO(로트번호)	ISSUED DATE(발행일자)
캠텍	0.1778*19.05	20260611 -01 ~ 37	2026-06-11
규격(재질)		LOT SIZE(수량)	
0.1778*19.05 STS305 BA	Au 0.254 μ m~ Ni 0.1 μ m	1,566 Kg	

I. VISUAL INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/5Reel)

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION
1	DISCOLORATION(변색)	0/1	OK	6	NO PLATING(미도금)
2	STAIN(얼룩)	0/1	OK	7	PEELING(도금 벗겨짐)
3	RUST(부식)	0/1	OK	8	LUMP(도금물침)
4	CONTAMINATION(오염)	0/1	OK	9	CAMBER(휨)
5	BENT(변형)	0/1	OK	10	PLATING BURR (도금)

II. DIMENSION INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/5Reel)

NO	항목/구분	SPEC			검사주기	우리하이피	
		규격	하한(-)	상한(+)		1차	2차
1	전폭	19.05	-0.127	0.127	Reel/Lot	18.958	
2	간격	5.08	-0.152	0.1524	Reel/Lot	5.069	
3	도금폭	1.52	-0.152	0.1524	Reel/Lot	1.602	
4	간격	6.60	-0.152	0.1524	Reel/Lot	6.607	
5							
6							
7							
8							
9							
10							

III. PLATING THICKNESS(도금두께) (Sampling Plan : 1y)

NO	SPECIFICATION	Measurement
1	X-Ray 측정	
	Au 0.254 μ m~ Ni 0.1 μ m	첨부 : 도금 첨부 : 도금

IV. FUNCTIONAL TEST (Sampling Plan : n=100mm/EA, 2EA/Shipping, c=0)

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
1	ADHESION TEST (밀착성 시험)	1.제품을 스카시 Tape에 부착 밀착후 45도 각도로 순간적으로 떼어낸다.(들뜸 및 벗겨짐) 2.테이프 시험이 안되는 제품은 니퍼로 90도로 상.하각은후 도금들뜸 이나 벗겨짐이 없을것.		OK
2	Chemical Deburring Test	1.Chemicals Phosphoric acid (85%) 20%, Nitric acid (60%) 5%, Hydrochloric acid (35%) 10%, DI Water 65% 2.Immersion time: 10 minutes 3.After immersion: Treated in an ultrasonic cleaner at 68-132 kHz for 20 minutes.		OK

제품 도면		우리 하이 피	작성	승인	종합 판정	
		고 객	작성	승인		

6/11

0.1778*19.05

① 48.3 ② 41.2 ③ 44.4
④ 50.8 ⑤ 42 ⑥ 50.4
⑦ 42 ⑧ 36.8 ⑨ 44.4
⑩ 44.8 ⑪ 44.65 ⑫ 50.2
⑬ 50.4 ⑭ 50.6 ⑮ 44.8
⑯ 42.2

⑰ 40.7 ⑱ 47.47 ⑲ 40
⑳ 35 ㉑ 44.4 ㉒ 44.3
㉓ 48.58 ㉔ 44.1 ㉕ 40
㉖ 44.7 ㉗ 44.8 ㉘ 44.2
㉙ 48.65 ㉚ 44.7 ㉛ 50.2
㉜ 44.28

총 1566kg