

Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	PLATING DATE(도금일자)	ISSUED DATE(발행일자)
넥스플러스	E 6S BUSBAR	260713-01	2026.07.13
MATERIAL(재질)	SPEC		수량
Al	Ni: 1.0~3.0 μ m Sn: 4.0~9.0 μ m		40 EA

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	V	6	BENT(변형)	0/1	V
2	STAIN(얼룩)	0/1	V	7	NO PLATING(미도금)	0/1	V
3	RUST(부식)	0/1	V	8			
4	CONTAMINATION(오염)	0/1	V	9			
5	PEELING(도금 벗겨짐)	0/1	V	10			


II.DIMENSION INSPECTION

NO	INSPECTION ITEMS	SPECIFICATION	MIN	MAX	AVERAGE	RESULT
11	PLATING THICKNESS (Ni)	1.0~3.0 μ m				
12	PLATING THICKNESS (Sn)	4.0~9.0 μ m				
13						
14						

도금두께 성적서 참조

III.FUNCTIONAL TEST

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
15	ADHESION TEST (밀착성 시험)	Not permit the peeling		OK
16				

FINAL RESULT	REMARK	PREPARED BY	CHECKED BY	APPROVED BY
		우데스		

(주)박스플러스



Ni: 1.0~3.0 μ m Sn: 4.0~9.0 μ m

품명 : E 6S BUSBAR LOT NO : 260713-01 일자 : 2026..07.13

FUNC: MEASURE
DATE: 2026-07-13
COL : 1.000 mm

$\frac{\text{Sn}}{\text{Ni}} \frac{\text{Al}}$
SEC : 15 Sec

No	μ m Sn	μ m Ni	Sn tolerance
1	6.181	1.401	5.971 6.245 6.518
2	6.008	1.399	
3	6.489	1.392	
4	6.027	1.354	
5	6.518	1.403	
Mean	6.245	1.390	
S.Dev	0.220	0.018	



도금원소 : Sn/Ni//Al

측정값 개수 5 5
최대값 6.518 1.403
최소값 6.008 1.354
범위 0.510 0.049
평균값 6.245 1.390
표준편차 0.220 0.018
변동계수 3.522 1.315

발행처 : 우리하이피

