



Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	LOT NO(로트번호)	ISSUED DATE(발행일자)
세종에이앤에스	0.15*159	20250407 -01 ~ 06	2025-04-07
규격(재질)		LOT SIZE(수량)	
0.15*159 Cu	Ni 1.0~2.0μm	615.3 Kg	

I. VISUAL INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea)

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS
1	DISCOLORATION(변색)	0/1	OK	6	NO PLATING(미도금)
2	STAIN(얼룩)	0/1	OK	7	PEELING(도금 벗겨짐)
3	RUST(부식)	0/1	OK	8	LUMP(도금물침)
4	CONTAMINATION(오염)	0/1	OK	9	CAMBER(휨)
5	BENT(변형)	0/1	OK	10	PLATING BURR (도금)

II. DIMENSION INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/Sheet)

NO	항목/구분	SPEC			검사주기	우리하이피	
		규격	하한(-)	상한(+)		1차	2차
1	전폭	159.0	-0.1		Reel/Lot	158.999	
2							
3							
4							
5							
6							
7							
8							
9							
10							

4/7
0.15 x 159
① 44.8 ④ 156.1
② 41.6 ⑤ 40.6
③ 41.6 ⑥ 40.6
총 615.3kg

III. PLATING THICKNESS(도금두께) (Sampling Plan : 1y)

NO	SPECIFICATION	Measurement Data	RESULT
1	X-Ray 측정 Ni 1.0~2.0μm	첨부 : 도금성적서 첨부 : 도금성적서	OK

IV. FUNCTION

NO	RESULT
1	OK

제품도면		우리하이피	작성	승인	종합판정	
		김영란	조승현			
고객		작성	승인	종합판정		

업체명 : 세종에이앤에스

품명 : 0.15x159 초물 LOT NO : 250407-01 DATE : 25.04.07.

No	μm Ni	Ni tolerance		
		1.258	1.343	1.429
1	1.365			
2	1.258			
3	1.402			
4	1.417			
5	1.275			
Mean	1.343			
S.Dev	0.073			


FUNC: MEASURE
COL : 0.100 mm

$\frac{\text{Ni}}{\text{Cu}}$

SEC : 15 Sec

평균값 1.343
표준편차 0.073
변동계수 5.431

우리하이피



업체명 : 세종에이앤에스


품명 : 0.15x159 종물 LOT NO : 250407-01 DATE : 25.04.07.

No	μm Ni	Ni tolerance
1	1.199	1.168 1.338 1.508
2	1.292	
3	1.368	
4	1.324	
5	1.508	
Mean	1.338	
S.Dev	0.113	

FUNC: MEASURE
COL : 0.100 mm

$\frac{\text{Ni}}{\text{Cu}}$

SEC : 15 Sec



도금원소 : Ni//Cu

측정값 개수 5

최대값 1.508

최소값 1.199

범위 0.309

평균값 1.338

표준편차 0.113

변동계수 8.474

우리하이피

