



Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	LOT NO(로트번호)	ISSUED DATE(발행일자)
(주)씨스파인	0.15*143	20241118 -01	2024-11-18
규격(재질)		LOT SIZE(수량)	
0.15*143 304 2H	Ni 1.7~3.0μm	103 Kg	

I. VISUAL INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/Shipping, c=0)							
NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	OK	6	NO PLATING(미도금)	0/1	OK
2	STAIN(얼룩)	0/1	OK	7	PEELING(도금 벗겨짐)	0/1	OK
3	RUST(부식)	0/1	OK	8	LUMP(도금물침)	0/1	OK
4	CONTAMINATION(오염)	0/1	OK	9	CAMBER(휨)	0/1	OK
5	BENT(변형)	0/1	OK	10	PLATING BURR (도금버)	0/1	OK

II. DIMENSION INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/Shipping, c=0)										
NO	항목/구분	SPEC			검사주기	우리하이피		고객		판정
		규격	하한(-)	상한(+)		1차	2차	1차	2차	
1	전폭	143.0	-0.1		Reel/Lot	142.951				OK
2										
3										
4										
5										
6										
7										
8										
9										
10										

III. PLATING THICKNESS(도금두께) (Sampling Plan : 1y				
NO	SPECIFICATION		Measurement Data	RESULT
1	X-Ray 측정		첨부 : 도금성적서	OK
		Ni 1.7~3.0μm	첨부 : 도금성적서	

IV. FUNCTIONAL TEST (		
NO	INSPECTION	RESULT
1	ADHESION (밀착성)	OK

제품 도면		우리 하이 피	작성	승인	종합 판정	
		고 객	작성	승인	종합 판정	

고객명: (주)씨스파인


품명 : 0.15X143 LOT NO : 241118-01 DATE : 24.11.18.

No	μm Ni	Ni tolerance		
		1.721	1.851	1.981
1	1.765			
2	1.907			
3	1.795			
4	1.766			
5	1.981			
6	1.891			
Mean	1.851			
S.Dev	0.089			

FUNC: MEASURE
COL : 0.100 mm

$\frac{\text{Ni}}{\text{SS}}$

SEC : 15 Sec



범위 0.216
평균값 1.851
표준편차 0.089
변동계수 4.796

우리하이피

