



Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	LOT NO(로트번호)	ISSUED DATE(발행일자)
신흥 SEC	0.4*30	20250421 -01 ~ 11	2025-04-21
규격(재질)		LOT SIZE(수량)	
0.4*30 AL	Ni 1.5 μ m ~	613 Kg	

I. VISUAL INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/SH)

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS
1	DISCOLORATION(변색)	0/1	OK	6	NO PLATING(미도금)
2	STAIN(얼룩)	0/1	OK	7	PEELING(도금 벗겨짐)
3	RUST(부식)	0/1	OK	8	LUMP(도금 뭉침)
4	CONTAMINATION(오염)	0/1	OK	9	CAMBER(휨)
5	BENT(변형)	0/1	OK	10	PLATING BURR (도금)

4/21

0.4 x 30

① ㄷ ② ㄷ ③ ㄷ ④ ㄷ

⑤ ㄷ ⑥ ㄷ ⑦ ㄷ ⑧ ㄷ

⑨ ㄷ ⑩ ㄷ ⑪ ㄷ ⑫ ㄷ

⑬ ㄷ ⑭ ㄷ

총 613kg

II. DIMENSION INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/SH)

NO	항목/구분	SPEC			검사주기	우리하이피	
		규격	하한(-)	상한(+)		1차	2차
1	전폭	30.0	-0.1		Reel/Lot	29.992	0.403
2						29.963	0.401
3						29.978	0.402
4						29.990	0.403
5						29.998	0.403
6						29.999	0.402
7						29.995	0.402
8						29.992	0.401
9						29.996	0.403
10						29.994	0.402

III. PLATING THICKNESS(도금두께) (Sampling Plan : 1y)

NO	SPECIFICATION		Measurement Data	RESULT
1	X-Ray 측정		첨부 : 도금성적서	OK
		Ni 1.5 μ m ~	첨부 : 도금성적서	

IV. FUNCTIONAL TEST (Sampling Plan : n=100mm/EA, 2EA/Shipping, c=0)

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
1	ADHESION TEST (밀착성 시험)	1.제품을 스카치 Tape에 완전 밀착후 45도 각도로 순간적으로 떼어낸다.(돌돌 및 벗겨짐) 2.테이프 시험이 안되는 제품은 니퍼로 90도로 상.하각은후 도금돌돌이나 벗겨짐이 없을것.		OK

제품도면



우리하이피	작성	승인	종합판정	
	김영란	조승현		
고객	작성	승인	종합판정	

고객명: 신흥SEC


품명 : 0.4X30 초물 LOT NO : 250421-01 DATE : 25.04.21.

No	μm Ni	Ni tolerance		
		2.035	2.068	2.100
1	2.058			
2	2.094			
3	2.065			
4	2.071			
5	2.035			
6	2.083			
Mean	2.068			
S.Dev	0.021			

FUNC: MEASURE
COL : 0.100 mm


Ni
—
Al

SEC : 15 Sec



도금원소 : Ni//Al

측정값 개수 6
최대값 2.094
최소값 2.035
범위 0.059
평균값 2.068
표준편차 0.021
변동계수 0.993



우리하이피(주)


고객명: 신흥SEC

품명 : 0.4X30 초물 LOT NO : 250421-11 DATE : 25.04.21.

No	μm Ni	Ni tolerance		
		2.042	2.070	2.098
1	2.052			
2	2.069			
3	2.072			
4	2.043			
5	2.085			
6	2.098			
Mean	2.070			
S.Dev	0.020			

FUNC: MEASURE
COL : 0.100 mm

$\frac{\text{Ni}}{\text{Al}}$
SEC : 15 Sec



도금원소 : Ni//Al
측정값 개수 6
최대값 2.098
최소값 2.043
범위 0.055
평균값 2.070
표준편차 0.020
변동계수 0.982

우리하이피(주)

