

Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	PLATING DATE(도금일자)	ISSUED DATE(발행일자)
㈜ 에스엠프로토	SAMPLE(busbar)	260921-01	2026.09.21
MATERIAL(재질)	SPEC		수량
Al	Ni: 1.0~3.0 μ m Sn: 5.0~ μ m		20 EA

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	V	6	BENT(변형)	0/1	V
2	STAIN(얼룩)	0/1	V	7	NO PLATING(미도금)	0/1	V
3	RUST(부식)	0/1	V	8			
4	CONTAMINATION(오염)	0/1	V	9			
5	PEELING(도금 벗겨짐)	0/1	V	10			


II.DIMENSION INSPECTION

NO	INSPECTION ITEMS	SPECIFICATION	MIN	MAX	AVERAGE	RESULT
11	PLATING THICKNESS (Ni)	1.0~3.0 μ m				
12	PLATING THICKNESS (Sn)	5.0~ μ m				
13						
14						

도금두께 성적서 참조

III.FUNCTIONAL TEST

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
15	ADHESION TEST (밀착성 시험)	Not permit the peeling		OK
16				

FINAL RESULT	REMARK	PREPARED BY	CHECKED BY	APPROVED BY
		우데스		

(주) 에스엠프로토

Ni: 1.0~3.0 μ m Sn: 5.0~ μ m

품명: SAMPLE(busbar)

LOT NO: 20260921-1



일자: 2026.09.21

No	μ m Sn	μ m Ni	Sn tolerance		
			5.240	5.486	5.732
1	5.607	2.058			
2	5.460	1.293			
3	5.307	1.291			
4	5.732	1.606			
5	5.324	1.562			
Mean	5.486	1.562			
S.Dev	0.164	0.281			

FUNC: MEASURE
DATE: 2026-09-21
COL : 0.400 mm

Sn
Ni
Al

SEC : 15 Sec



도금원소 : Sn/Ni//Al

측정값 개수	5	5
최대값	5.732	2.058
최소값	5.307	1.291
범위	0.425	0.767
평균값	5.486	1.562
표준편차	0.164	0.281
변동계수	2.985	17.966

우리하이피

