



Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	LOT NO(로트번호)	ISSUED DATE(발행일자)
풍산	0.15*175	20260822 -01 ~ 02	2026-08-22
규격(재질)		LOT SIZE(수량)	
0.15*175 Cu	Ni 1.0~2.0µm	658.4kg	

I. VISUAL INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/5Reel)

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS
1	DISCOLORATION(변색)	0/1	OK	6	NO PLATING(미도금)
2	STAIN(얼룩)	0/1	OK	7	PEELING(도금 벗겨짐)
3	RUST(부식)	0/1	OK	8	LUMP(도금물침)
4	CONTAMINATION(오염)	0/1	OK	9	CAMBER(휨)
5	BENT(변형)	0/1	OK	10	PLATING BURR (도금)

II. DIMENSION INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/5Reel)

NO	항목/구분	SPEC			검사주기	우리하이피	
		규격	하한(-)	상한(+)		1차	2차
1	전폭	175.0	-0.1		Reel/Lot	174.998	
2							
3							
4							
5							
6							
7							
8							
9							
10							

III. PLATING THICKNESS(도금두께) (Sampling Plan : 1y)

NO	SPECIFICATION	Measurement Data	RESULT
1	X-Ray 측정 Ni 1.0~2.0µm	첨부 : 도금성적서	OK
		첨부 : 도금성적서	

NO	RESULT
1	OK

제품도면		리하이피	김영란	조승현	합판정	
		고객	작성	승인	종합판정	

업체명 : 풍산

품명 : 0.15x175 초물 LOT NO : 260822-01 DATE : 26.08.22.

No	μm Ni	Ni tolerance		
		1.343	1.418	1.493
1	1.386			
2	1.395			
3	1.410			
4	1.405			
5	1.493			
Mean	1.418			
S.Dev	0.043			


FUNC: MEASURE
COL : 0.100 mm

$\frac{\text{Ni}}{\text{Cu}}$

SEC : 20 Sec

평균값 1.418
표준편차 0.043
변동계수 3.036

우리하이피



업체명 : 풍산


품명 : 0.15x175 종물 LOT NO : 260822-01 DATE : 26.08.22.

No	μm Ni	Ni tolerance
1	1.439	1.370 1.477 1.584
2	1.470	
3	1.584	
4	1.450	
5	1.443	
Mean	1.477	
S.Dev	0.061	

FUNC: MEASURE
COL : 0.100 mm

$\frac{\text{Ni}}{\text{Cu}}$

SEC : 20 Sec



도금원소 : Ni//Cu

측정값 개수 5

최대값 1.584

최소값 1.439

범위 0.145

평균값 1.477

표준편차 0.061

변동계수 4.121

우리하이피

