



Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	LOT NO(로트번호)	ISSUED DATE(발행일자)
세종에이앤에스	0.15*175	20260406 -01 ~ 04	2026-04-06
규격(재질)		LOT SIZE(수량)	
0.15*175 Cu	Ni 1.0~2.0μm	994.2 Kg	

I. VISUAL INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/5Reel)

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION
1	DISCOLORATION(변색)	0/1	OK	6	NO PLATING(미도금)
2	STAIN(얼룩)	0/1	OK	7	PEELING(도금 벗겨짐)
3	RUST(부식)	0/1	OK	8	LUMP(도금 뭉침)
4	CONTAMINATION(오염)	0/1	OK	9	CAMBER(휨)
5	BENT(변형)	0/1	OK	10	PLATING BURR (도금)

II. DIMENSION INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/5Reel)

NO	항목/구분	SPEC			검사주기	우리하이피	
		규격	하한(-)	상한(+)		1차	2차
1	전폭	175.0	-0.1		Reel/Lot	174.999	
2							
3							
4							
5							
6							
7							
8							
9							
10							

4/6
0.15 x 175
① 270.8
② 270.8
③ 226.3
④ 226.3
총 994.2kg

III. PLATING THICKNESS(도금두께) (Sampling Plan : 1y)

NO	SPECIFICATION	Measurement Data	RESULT
1	X-Ray 측정	첨부 : 도금성적서	OK
	Ni 1.0~2.0μm	첨부 : 도금성적서	

IV. FURTHER INSPECTION

NO		RESULT
1		OK

제품도면

0.15*175

175.0

리
하
이
피

고
객

김영란

조승현

합
판
정

2026-04-06
우리하이피(주)
Q.C

작성

승인

총
합
판
정

업체명 : 세종에이앤에스

품명 : 0.15*175 초물 LOT NO : 260406-01 DATE : 26.04.06.

No	μm Ni	Ni tolerance		
		1.282	1.362	1.443
1	1.359			
2	1.374			
3	1.443			
4	1.302			
5	1.334			
Mean	1.362			
S.Dev	0.053			


FUNC: MEASURE
COL : 0.100 mm

$\frac{\text{Ni}}{\text{Cu}}$

SEC : 20 Sec

평균값 1.362
표준편차 0.053
변동계수 3.866

우리하이피



업체명 : 세종에이앤에스

품명 : 0.15*175

종물

LOT NO : 260406-01


DATE : 26.04.06.

No	μm Ni	Ni tolerance	
		1.269	1.325 1.382
1	1.269		
2	1.323		
3	1.276		
4	1.381		
5	1.378		
Mean	1.325		
S.Dev	0.054		

FUNC: MEASURE
COL : 0.100 mm

$\frac{\text{Ni}}{\text{Cu}}$

SEC : 20 Sec



도금원소 : Ni//Cu

측정값 개수 5

최대값 1.381

최소값 1.269

범위 0.112

평균값 1.325

표준편차 0.054

변동계수 4.043

우리하이피

