



Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	LOT NO(로트번호)	ISSUED DATE(발행일자)
세종에이앤에스	0.15*187	20260416 -01 ~ 02	2026-04-16
규격(재질)		LOT SIZE(수량)	
0.15*187 Cu	Ni 1.0~2.0μm	714.6 Kg	

I. VISUAL INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/S)

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION
1	DISCOLORATION(변색)	0/1	OK	6	NO PLATING(미도금)
2	STAIN(얼룩)	0/1	OK	7	PEELING(도금 벗겨짐)
3	RUST(부식)	0/1	OK	8	LUMP(도금물침)
4	CONTAMINATION(오염)	0/1	OK	9	CAMBER(휨)
5	BENT(변형)	0/1	OK	10	PLATING BURR (도금)

II. DIMENSION INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/S)

NO	항목/구분	SPEC			검사주기	우리하이피	
		규격	하한(-)	상한(+)		1차	2차
1	전폭	187.0	-0.1		Reel/Lot	186.997	
2							
3							
4							
5							
6							
7							
8							
9							
10							

4/16

0.15 x 187

① 347.3

② 347.3

총 714.6kg

III. PLATING THICKNESS(도금두께) (Sampling Plan : 1y)

NO	SPECIFICATION	Measurement Data	RESULT
1	X-Ray 측정 Ni 1.0~2.0μm	첨부 : 도금성적서	OK
		첨부 : 도금성적서	


SULT

OK

제품도면	0.15*187	187.0	리하이피	김영란	조승현	종합판정	2026-04-16 우리하이피(주) Q.C
			고객	작성	승인	종합판정	

업체명 : 세종에이앤에스

품명 : 0.15*187 초물 LOT NO : 260416-01 DATE : 26.04.16.

No	μm Ni		Ni tolerance	
			1.214	1.301 1.389
1	1.251			
2	1.253			
3	1.338			
4	1.389			
5	1.276			
Mean	1.301			
S.Dev	0.060			


FUNC: MEASURE
COL : 0.100 mm

$\frac{\text{Ni}}{\text{Cu}}$

SEC : 20 Sec

평균값 1.301
표준편차 0.060
변동계수 4.633

우리하이피




업체명 : 세종에이앤에스

품명 : 0.15*187 종물 LOT NO : 260416-01 DATE : 26.04.16.

No	μm Ni	Ni tolerance
1	1.305	1.280 1.308 1.336
2	1.323	
3	1.280	
4	1.320	
5	1.312	
Mean	1.308	
S.Dev	0.017	

FUNC: MEASURE
COL : 0.100 mm

$\frac{\text{Ni}}{\text{Cu}}$
SEC : 20 Sec



도금원소 : Ni//Cu
측정값 개수 5
최대값 1.323
최소값 1.280
범위 0.043
평균값 1.308
표준편차 0.017
변동계수 1.312

우리하이피

