



Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	LOT NO(로트번호)	ISSUED DATE(발행일자)
신흥 SEC	0.4*26	20251021 -01 ~ 05	2025-10-21
규격(재질)		LOT SIZE(수량)	
0.4*26 AL	Ni 1.5 μ m ~	245 Kg	

I. VISUAL INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea)

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION
1	DISCOLORATION(변색)	0/1	OK	6	NO PLATING(미도금)
2	STAIN(얼룩)	0/1	OK	7	PEELING(도금 벗겨짐)
3	RUST(부식)	0/1	OK	8	LUMP(도금응집)
4	CONTAMINATION(오염)	0/1	OK	9	CAMBER(휨)
5	BENT(변형)	0/1	OK	10	PLATING BURR (도금)

II. DIMENSION INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/S

NO	항목/구분	SPEC			검사주기	우리하이피	
		규격	하한(-)	상한(+)		1차	2차
1	전폭	26.0	-0.1		Reel/Lot	25.992	0.402
2						25.996	0.403
3						25.984	0.402
4						25.998	0.403
5						25.997	0.403
6							
7							
8							
9							
10							

III. PLATING THICKNESS(도금두께) (Sampling Plan : 1y

NO	SPECIFICATION		Measurement Data	RESULT
1	X-Ray 측정		첨부 : 도금성적서	OK
		Ni 1.5 μ m ~	첨부 : 도금성적서	

10/21

0.4*26

① 4t ④ 4t

② 4t ⑤ 4t

③ 4t

총 245kg

업체명 : 신흥SEC


품명 : 0.4X26 초물 LOT NO : 251021-01 DATE : 25.10.21.

No	μm Ni	Ni tolerance	
		2.006	2.035 2.064
1	2.023		
2	2.006		
3	2.017		
4	2.058		
5	2.042		
6	2.064		
Mean	2.035		
S.Dev	0.023		


FUNC: MEASURE
COL : 0.100 mm

$\frac{\text{Ni}}{\text{Al}}$

SEC : 15 Sec



도금원소 : Ni//Al
측정값 개수 6
최대값 2.064
최소값 2.006
범위 0.058
평균값 2.035
표준편차 0.023
변동계수 1.148



우리하이피

업체명 : 신흥SEC


품명 : 0.4X26 초물 LOT NO : 251021-05 DATE : 25.10.21.

No	μm Ni	Ni tolerance	
		2.007	2.030 2.053
1	2.008		
2	2.031		
3	2.027		
4	2.018		
5	2.042		
6	2.053		
Mean	2.030		
S.Dev	0.016		

FUNC: MEASURE
COL : 0.100 mm

$\frac{\text{Ni}}{\text{Al}}$

SEC : 15 Sec



도금원소 : Ni//Al
측정값 개수 6
최대값 2.053
최소값 2.008
범위 0.045
평균값 2.030
표준편차 0.016
변동계수 0.798

우리하이피

