



Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	LOT NO(로트번호)	ISSUED DATE(발행일자)
신흥 SEC	0.4*26	20260211 -01 ~ 07	2026-02-11
규격(재질)		LOT SIZE(수량)	
0.4*26 AL	Ni 1.5 μ m ~	343 Kg	

I. VISUAL INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/5Reel)

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION
1	DISCOLORATION(변색)	0/1	OK	6	NO PLATING(미도금)
2	STAIN(얼룩)	0/1	OK	7	PEELING(도금 벗겨짐)
3	RUST(부식)	0/1	OK	8	LUMP(도금물침)
4	CONTAMINATION(오염)	0/1	OK	9	CAMBER(휨)
5	BENT(변형)	0/1	OK	10	PLATING BURR (도금)

II. DIMENSION INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/5Reel)


NO	항목/구분	SPEC			검사주기	우리하이피	
		규격	하한(-)	상한(+)		1차	2차
1	전폭	26.0	-0.1		Reel/Lot	25.970	0.402
2						25.971	0.403
3						25.976	0.403
4						25.996	0.403
5						25.980	0.403
6						25.960	0.402
7						25.979	0.402
8							
9							
10							


2/11
0.4x26
① 4P ⑤ 4P
② 4P ⑥ 4P
③ 4P ⑦ 4P
④ 4P
총 343kg

III. PLATING THICKNESS(도금두께) (Sampling Plan : 1y)

NO	SPECIFICATION		Measurement Data	RESULT
1	X-Ray 측정	Ni 1.5 μ m ~	첨부 : 도금성적서 첨부 : 도금성적서	OK

IV. FUNCTIONAL TEST (Sampling Plan : n=100mm/EA, 2EA/Shipping, c=0)

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
1	ADHESION TEST (밀착성 시험)	1.제품을 스카치 Tape에 완전 밀착후 45도 각도로 순간적으로 떼어낸다.(돌돌 및 벗겨짐) 2.테이프 시험이 안되는 제품은 니퍼로 90도로 상.하각은후 도금돌돌이나 벗겨짐이 없을것.		OK

제품도면		우리하이피	작성	승인	종합판정	
			김영란	조승현		
		고객	작성	승인	종합판정	


업체명 : 신흥SEC

품명 : 0.4x26 초물 LOT NO : 260211-01 DATE : 26.02.11.

No	μm Ni	Ni tolerance
1	2.017	2.003 2.043 2.083
2	2.058	
3	2.046	
4	2.023	
5	2.031	
6	2.083	
Mean	2.043	
S.Dev	0.025	


FUNC: MEASURE
COL : 0.100 mm

$\frac{\text{Ni}}{\text{Al}}$
SEC : 15 Sec



도금원소 : Ni//Al
측정값 개수 6
최대값 2.083
최소값 2.017
범위 0.066
평균값 2.043
표준편차 0.025
변동계수 1.210

우리하이피



업체명 : 신흥SEC


품명 : 0.4x26 초물 LOT NO : 260211-07 DATE : 26.02.11.

No	μm Ni	Ni tolerance		
		2.035	2.066	2.097
1	2.075			
2	2.081			
3	2.035			
4	2.094			
5	2.049			
6	2.063			
Mean	2.066			
S.Dev	0.022			

FUNC: MEASURE
COL : 0.100 mm

$\frac{\text{Ni}}{\text{Al}}$

SEC : 15 Sec



도금원소 : Ni//Al

측정값 개수 6

최대값 2.094


최소값 2.035

범위 0.059

평균값 2.066

표준편차 0.022

변동계수 1.049



우리하이피

업체명 : 신흥SEC


품명 : 0.4x26 초물 LOT NO : 260211-07 DATE : 26.02.11.

No	μm Ni	Ni tolerance		
		2.035	2.066	2.097
1	2.075			
2	2.081			
3	2.035			
4	2.094			
5	2.049			
6	2.063			
Mean	2.066			
S.Dev	0.022			

FUNC: MEASURE
COL : 0.100 mm


Ni
—
Al

SEC : 15 Sec



도금원소 : Ni//Al

측정값 개수 6
최대값 2.094
최소값 2.035
범위 0.059
평균값 2.066
표준편차 0.022
변동계수 1.049



우리하이피