



Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	LOT NO(로트번호)	ISSUED DATE(발행일자)
세종에이앤에스	0.15*168	20250425 -01 ~ 03	2025-04-25
규격(재질)		LOT SIZE(수량)	
0.15*168 Cu	Ni 1.0~2.0μm	295Kg	

I. VISUAL INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea)

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION
1	DISCOLORATION(변색)	0/1	OK	6	NO PLATING(미도금)
2	STAIN(얼룩)	0/1	OK	7	PEELING(도금 벗겨짐)
3	RUST(부식)	0/1	OK	8	LUMP(도금 뭉침)
4	CONTAMINATION(오염)	0/1	OK	9	CAMBER(휨)
5	BENT(변형)	0/1	OK	10	PLATING BURR (도금)

II. DIMENSION INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/S

NO	항목/구분	SPEC			검사주기	우리하이피	
		규격	하한(-)	상한(+)		1차	2차
1	전폭	168.0	-0.1		Reel/Lot	167.997	
2							
3							
4							
5							
6							
7							
8							
9							
10							

III. PLATING THICKNESS(도금두께) (Sampling Plan : 1y

NO	SPECIFICATION	Measurement Data	RESULT
1	X-Ray 측정 Ni 1.0~2.0μm	첨부 : 도금성적서	OK
		첨부 : 도금성적서	

IV. FUNCTIONAL

NO		RESULT
1		OK

제품도면		리하이피	김영란	조승현	종합판정	
		고객	작성	승인	종합판정	

업체명 : 세종에이앤에스

품명 : 0.15x168 초물 LOT NO : 250425-01 DATE : 25.04.25.

No	μm Ni		Ni tolerance		
			1.302	1.390	1.477
1	1.395				
2	1.367				
3	1.390				
4	1.319				
5	1.477				
Mean	1.390				
S.Dev	0.057				


FUNC: MEASURE
COL : 0.100 mm

$\frac{\text{Ni}}{\text{Cu}}$

SEC : 15 Sec

표준편차 0.057
변동계수 4.128

우리하이피




업체명 : 세종에이앤에스

품명 : 0.15x168 종물 LOT NO : 250425-01 DATE : 25.04.25.

No	μm Ni	Ni tolerance
1	1.365	1.365 1.440 1.515
2	1.450	
3	1.502	
4	1.457	
5	1.425	
Mean	1.440	
S.Dev	0.050	

FUNC: MEASURE
COL : 0.100 mm

$\frac{\text{Ni}}{\text{Cu}}$
SEC : 15 Sec



도금원소 : Ni//Cu
측정값 개수 5
최대값 1.502
최소값 1.365
범위 0.137
평균값 1.440
표준편차 0.050
변동계수 3.487

우리하이피

