



Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	LOT NO(로트번호)	ISSUED DATE(발행일자)
세종에이앤에스	0.15*159	20250502 -01 ~ 02	2025-05-02
규격(재질)		LOT SIZE(수량)	
0.15*159 Cu	Ni 1.0~2.0μm	452.2 Kg	

I. VISUAL INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/S)

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION
1	DISCOLORATION(변색)	0/1	OK	6	NO PLATING(미도금)
2	STAIN(얼룩)	0/1	OK	7	PEELING(도금 벗겨짐)
3	RUST(부식)	0/1	OK	8	LUMP(도금물침)
4	CONTAMINATION(오염)	0/1	OK	9	CAMBER(휨)
5	BENT(변형)	0/1	OK	10	PLATING BURR (도금)

II. DIMENSION INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/S)

NO	항목/구분	SPEC			검사주기	우리하이피	
		규격	하한(-)	상한(+)		1차	2차
1	전폭	159.0	-0.1		Reel/Lot	158.997	
2							
3							
4							
5							
6							
7							
8							
9							
10							

III. PLATING THICKNESS(도금두께) (Sampling Plan : 1y)

NO	SPECIFICATION	Measurement Data	RESULT
1	X-Ray 측정 Ni 1.0~2.0μm	첨부 : 도금성적서	OK
		첨부 : 도금성적서	

IV. FUNCTION

NO	RESULT
1	OK

제품도면		리하이피	김영란	조승현	종합판정	
		고객	작성	승인	종합판정	

업체명 : 세종에이앤에스

품명 : 0.15x159 초물 LOT NO : 250502-01 DATE : 25.05.02.

No	μm Ni	Ni tolerance		
		1.381	1.517	1.653
1	1.443			
2	1.472			
3	1.653			
4	1.491			
5	1.526			
Mean	1.517			
S.Dev	0.082			


FUNC: MEASURE
COL : 0.100 mm

$\frac{\text{Ni}}{\text{Cu}}$

SEC : 15 Sec

표준편차 0.082
변동계수 5.391

우리하이피



업체명 : 세종에이앤에스


품명 : 0.15x159 종물 LOT NO : 250502-01 DATE : 25.05.02.

No	μm Ni	Ni tolerance
1	1.417	1.340 1.434 1.528
2	1.388	
3	1.528	
4	1.424	
5	1.412	
Mean	1.434	
S.Dev	0.054	

FUNC: MEASURE
COL : 0.100 mm

$\frac{\text{Ni}}{\text{Cu}}$

SEC : 15 Sec



도금원소 : Ni//Cu

측정값 개수 5

최대값 1.528

최소값 1.388

범위 0.140

평균값 1.434

표준편차 0.054

변동계수 3.792

우리하이피

