

# Quality Assurance Report

| CUSTOMER(고객명) | DESCRIPTION(품명)       | PLATING DATE(도금일자) | ISSUED DATE(발행일자) |
|---------------|-----------------------|--------------------|-------------------|
| 에스코백          | DUMMY-D938468         | 20260918-1         | 2026.09.18        |
| MATERIAL(재질)  | SPEC                  |                    | 수량                |
| Al            | Nip : 2.0~4.0 $\mu$ m |                    | 36,000 EA         |

## I. VISUAL INSPECTION

| NO | INSPECTION ITEMS  | Ac/Re | RESULT | NO | INSPECTION ITEMS | Ac/Re | RESULT |
|----|-------------------|-------|--------|----|------------------|-------|--------|
| 1  | DISCOLORATION(변색) | 0/1   | V      | 6  | BENT(변형)         | 0/1   | V      |
| 2  | STAIN(얼룩)         | 0/1   | V      | 7  | NO PLATING(미도금)  | 0/1   | V      |
| 3  | RUST(부식)          | 0/1   | V      | 8  |                  |       |        |
| 4  | CONTAMINATION(오염) | 0/1   | V      | 9  |                  |       |        |
| 5  | PEELING(도금 벗겨짐)   | 0/1   | V      | 10 |                  |       |        |


## II. DIMENSION INSPECTION

| NO | INSPECTION ITEMS        | SPECIFICATION   | MIN | MAX | AVERAGE | RESULT |
|----|-------------------------|-----------------|-----|-----|---------|--------|
| 11 | PLATING THICKNESS (Nip) | 2.0~4.0 $\mu$ m |     |     |         |        |
| 12 |                         |                 |     |     |         |        |
| 13 |                         |                 |     |     |         |        |
| 14 |                         |                 |     |     |         |        |

도금두께 성적서 참조

## III. FUNCTIONAL TEST

| NO | INSPECTION ITEMS          | SPECIFICATION          | TEST SAMPLE | RESULT |
|----|---------------------------|------------------------|-------------|--------|
| 15 | ADHESION TEST<br>(밀착성 시험) | Not permit the peeling |             | OK     |
| 16 |                           |                        |             |        |

| FINAL RESULT                                                                        | REMARK | PREPARED BY | CHECKED BY                                                                            | APPROVED BY                                                                           |
|-------------------------------------------------------------------------------------|--------|-------------|---------------------------------------------------------------------------------------|---------------------------------------------------------------------------------------|
|  |        | 고은채         |  |  |

에스코빅 Nip : 2.0~4.0 $\mu$ m


품명 : DUMMY D-938468 LOT NO : 20260918-1 일자 : 2026.09.18

| No    | $\mu$ m<br>NiP | NiP tolerance |       |       |
|-------|----------------|---------------|-------|-------|
|       |                | 2.811         | 2.880 | 2.949 |
| 1     | 2.868          |               |       |       |
| 2     | 2.949          |               |       |       |
| 3     | 2.871          |               |       |       |
| 4     | 2.875          |               |       |       |
| 5     | 2.836          |               |       |       |
| Mean  | 2.880          |               |       |       |
| S.Dev | 0.037          |               |       |       |

FUNC: MEASURE  
DATE: 2026-09-18  
COL : 1.000 mm

$\frac{\text{NiP}}{\text{Al}}$

SEC : 15 Sec



도금원소 : NiP//Al

측정값 개수 5

최대값 2.949

최소값 2.836

범위 0.113

평균값 2.880

표준편차 0.037

변동계수 1.294

발행처 : 우리하이피

