



Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	LOT NO(로트번호)	ISSUED DATE(발행일자)
풍산	0.1*163	63CX5B0A11~	2026-09-17
규격(재질)		LOT SIZE(수량)	
0.1*163 CU	Ni 1.0~2.0μm	836.5 Kg	

I. VISUAL INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/Shipping, c=0)							
NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	OK	6	NO PLATING(미도금)	0/1	OK
2	STAIN(얼룩)	0/1	OK	7	PEELING(도금 벗겨짐)	0/1	OK
3	RUST(부식)	0/1	OK	8	LUMP(도금물침)	0/1	OK
4	CONTAMINATION(오염)	0/1	OK	9	CAMBER(휨)	0/1	OK
5	BENT(변형)	0/1	OK	10	PLATING BURR (도금버)	0/1	OK

II. DIMENSION INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/Shipping, c=0)							
NO	항목/구분	SPEC			검사주기	우리하이피	
		규격	하한(-)	상한(+)		1차	2차
1	전폭	163.0	-0.1		Reel/Lot	163.090	
2	1) 63CX5B0A11 / 260915-1					163.080	
3	2) 63CX5B0A12 / 260916-1					163.080	
4	3) 63B54B0A2 / 260916-2					163.090	
5	4) 63B54B0A2 / 260917-1						
6							
7							
8							
9							
10							

9/11 (0.1 X 63)

9 285.5

10 298

11 139.5

12 113.5

13 836.5kg

III. PLATING THICKNESS(도금두께) (Sampling Plan : 1Y)			
NO	SPECIFICATION	Measurment	
1	X-Ray 측정	첨부 : 도금성적서	OK
	Ni 1.0~2.0μm	첨부 : 도금성적서	

IV. FUNCTIONAL TEST (Sampling Plan : n=100mm/EA, 2EA/Shipping, c=0)				
NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
1				OK

제품도면		우리하이피	작성	승인	종합판정	
			심문경	조승현		
		고객	작성	승인	종합판정	


업체명 : 풍산

품명 : 0.1x163 초물 LOT NO : 63CX5B0A11 DATE : 26.09.15

No	μm Ni	Ni tolerance	
		1.438	1.510
1	1.446		
2	1.469		
3	1.510		
4	1.447		
5	1.497		
Mean	1.474		
S.Dev	0.029		

FUNC: MEASURE
COL : 0.100 mm

$\frac{\text{Ni}}{\text{Cu}}$
SEC : 20 Sec



도금원소 : Ni//Cu
측정값 개수 5
최대값 1.510
최소값 1.446
범위 0.064
평균값 1.474
표준편차 0.029
변동계수 1.967

우리하이피



업체명 : 풍산


품명 : 0.1x163 중물 LOT NO : 63CX5B0A11 DATE : 26.09.15

No	μm Ni		Ni	tolerance	
				1.449	1.501
1	1.462				
2	1.466				
3	1.501				
4	1.467				
5	1.480				
Mean	1.475				
S.Dev	0.016				

FUNC: MEASURE
COL : 0.100 mm

Ni
Cu

SEC : 20 Sec



도금원소 : Ni//Cu
측정값 개수 5
최대값 1.501
최소값 1.462
범위 0.039
평균값 1.475
표준편차 0.016
변동계수 1.080

우리하이피

