



Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	LOT NO(로트번호)	ISSUED DATE(발행일자)
신흥 SEC	0.4*26	20260817 -01 ~ 11	2026-08-17
규격(재질)		LOT SIZE(수량)	
0.4*26 AL	Ni 1.5 μ m ~	616 Kg	

I. VISUAL INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/S)

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION
1	DISCOLORATION(변색)	0/1	OK	6	NO PLATING(미도금)
2	STAIN(일록)	0/1	OK	7	PEELING(도금 벗겨짐)
3	RUST(부식)	0/1	OK	8	LUMP(도금물침)
4	CONTAMINATION(오염)	0/1	OK	9	CAMBER(휨)
5	BENT(변형)	0/1	OK	10	PLATING BURR (도금)

8/17

0.4X26

① ㄱ ② ㄴ ③ ㄷ
④ ㄹ ⑤ ㅁ ⑥ ㅂ ⑦ ㅅ
⑧ ㅈ ⑨ ㅊ ⑩ ㅋ
⑪ ㆁ ⑫ ㆂ

총 616kg

II. DIMENSION INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/S)

NO	항목/구분	SPEC			검사주기	우리하이피	
		규격	하한(-)	상한(+)		1차	2차
1	전폭	26.0	-0.1		Reel/Lot	25.950	0.401
2						25.956	0.402
3						25.952	0.401
4						25.978	0.401
5						25.943	0.403
6						25.941	0.401
7						25.992	0.402
8						25.988	0.403
9						25.986	0.402
10						25.994	0.401

III. PLATING THICKNESS(도금두께) (Sampling Plan : 1y)

NO	SPECIFICATION		Measurement Data	RESULT
1	X-Ray 측정	Ni 1.5 μ m ~	첨부 : 도금성적서 첨부 : 도금성적서	OK

IV. FUNCTIONAL TEST (Sampling Plan : n=100mm/EA, 2EA/Shipping, c=0)

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
1	ADHESION TEST (밀착성 시험)	1.제품을 스카치 Tape에 완전 밀착후 45도 각도로 순간적으로 떼어낸다.(들뜸 및 벗겨짐) 2.테이프 시험이 안되는 제품은 니퍼로 90도로 상.하각은후 도금들뜸 이나 벗겨짐이 없을것.		OK

제품도면		우리하이피	작성	승인	종합판정	
		김영란		조승현		
고객		작성		승인	종합판정	

업체명 : 신흥SEC


품명 : 0.4x26 초물 LOT NO : 260817-01 DATE : 26.08.17.

No	μm Ni	Ni tolerance
1	2.082	2.044 2.071 2.098
2	2.076	
3	2.047	
4	2.090	
5	2.044	
6	2.088	
Mean	2.071	
S.Dev	0.020	


FUNC: MEASURE
COL : 0.100 mm

Ni
—
Al

SEC : 15 Sec



도금원소 : Ni//Al
측정값 개수 6
최대값 2.090
최소값 2.044
범위 0.046
평균값 2.071
표준편차 0.020
변동계수 0.990



우리하이피

업체명 : 신흥SEC


품명 : 0.4x26 초물 LOT NO : 260817-11 DATE : 26.08.17.

No	μm Ni	Ni tolerance
1	2.066	2.017 2.041 2.066
2	2.036	
3	2.043	
4	2.027	
5	2.051	
6	2.025	
Mean	2.041	
S.Dev	0.016	

FUNC: MEASURE
COL : 0.100 mm

Ni
—
Al

SEC : 15 Sec



도금원소 : Ni//Al
측정값 개수 6
최대값 2.066
최소값 2.025
범위 0.041
평균값 2.041
표준편차 0.016
변동계수 0.761

우리하이피

