

Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	PLATING DATE(도금일자)	ISSUED DATE(발행일자)
에스코백	DUMMY-D9257325	20261002-1	2026.10.02
MATERIAL(재질)	SPEC		수량
AI	Nip : 2.0~4.0 μ m		2,690 EA

I.VISUAL INSPECTION

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	V	6	BENT(변형)	0/1	V
2	STAIN(얼룩)	0/1	V	7	NO PLATING(미도금)	0/1	V
3	RUST(부식)	0/1	V	8			
4	CONTAMINATION(오염)	0/1	V	9			
5	PEELING(도금 벗겨짐)	0/1	V	10			


II.DIMENSION INSPECTION

NO	INSPECTION ITEMS	SPECIFICATION	MIN	MAX	AVERAGE	RESULT
11	PLATING THICKNESS (Nip)	2.0~4.0 μ m				
12						
13						
14						

도금두께 성적서 참조

III.FUNCTIONAL TEST

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
15	ADHESION TEST (말착성 시험)	Not permit the peeling		OK
16				

FINAL RESULT	REMARK	PREPARED BY	CHECKED BY	APPROVED BY
		고은채	/	

에스코백 Nip : 2.0~4.0 μ m


품명: DUMMY-D9257325 LOT NO: 20261002-1 일자: 2026.10.02

No	μ m NiP	NiP tolerance	
		2.560	2.704 2.847
1	2.612		
2	2.677		
3	2.678		
4	2.847		
5	2.704		
Mean	2.704		
S.Dev	0.078		

FUNC: MEASURE
DATE: 2026-10-02
COL : 1.000 mm

$\frac{\text{NiP}}{\text{Al}}$

SEC : 15 Sec



도금원소 : NiP//Al
측정값 개수 5
최대값 2.847
최소값 2.612
범위 0.235
평균값 2.704
표준편차 0.078
변동계수 2.880

우리하이피

