

Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	PLATING DATE(도금일자)	ISSUED DATE(발행일자)
에스코백	DUMMY-D9787447	20261002-1	2026.10.02
MATERIAL(재질)	SPEC		수량
Al	Nip : 2.0~4.0 μ m		10,000 EA

I.VISUAL INSPECTION

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	V	6	BENT(변형)	0/1	V
2	STAIN(일룩)	0/1	V	7	NO PLATING(미도금)	0/1	V
3	RUST(부식)	0/1	V	8			
4	CONTAMINATION(오염)	0/1	V	9			
5	PEELING(도금 벗겨짐)	0/1	V	10			

II.DIMENSION INSPECTION

NO	INSPECTION ITEMS	SPECIFICATION	MIN	MAX	AVERAGE	RESULT
11	PLATING THICKNESS (Nip)	2.0~4.0 μ m				
12						
13						
14						

도금두께 성적서 참조

III.FUNCTIONAL TEST

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
15	ADHESION TEST (밀착성 시험)	Not permit the peeling		OK
16				

FINAL RESULT	REMARK	PREPARED BY	CHECKED BY	APPROVED BY
		고은채		

에스코빅 Nip : 2.0~4.0 μ m


품명: DUMMY-D9787447 LOT NO: 20261002-1 일자: 2026.10.02

No	μ m NiP	NiP tolerance		
		2.588	2.724	2.860
1	2.713			
2	2.628			
3	2.860			
4	2.776			
5	2.644			
Mean	2.724			
S.Dev	0.086			

FUNC: MEASURE
DATE: 2026-10-02
COL : 1.000 mm

$\frac{\text{NiP}}{\text{Al}}$

SEC : 15 Sec



도금원소 : NiP//Al

측정값 개수 5

최대값 2.860

최소값 2.628

범위 0.232

평균값 2.724

표준편차 0.086

변동계수 3.155

우리하이피

