

# Quality Assurance Report

|               |                       |                    |                   |
|---------------|-----------------------|--------------------|-------------------|
| CUSTOMER(고객명) | DESCRIPTION(품명)       | PLATING DATE(도금일자) | ISSUED DATE(발행일자) |
| 에스코백          | DUMMY-D938468         | 20261006-1         | 2026.10.06        |
| MATERIAL(재질)  | SPEC                  |                    | 수량                |
| Al            | Nip : 2.0~4.0 $\mu$ m |                    | 45,000 EA         |

## I.VISUAL INSPECTION

| NO | INSPECTION ITEMS  | Ac/Re | RESULT | NO | INSPECTION ITEMS | Ac/Re | RESULT |
|----|-------------------|-------|--------|----|------------------|-------|--------|
| 1  | DISCOLORATION(변색) | 0/1   | V      | 6  | BENT(변형)         | 0/1   | V      |
| 2  | STAIN(얼룩)         | 0/1   | V      | 7  | NO PLATING(미도금)  | 0/1   | V      |
| 3  | RUST(부식)          | 0/1   | V      | 8  |                  |       |        |
| 4  | CONTAMINATION(오염) | 0/1   | V      | 9  |                  |       |        |
| 5  | PEELING(도금 벗겨짐)   | 0/1   | V      | 10 |                  |       |        |


## II.DIMENSION INSPECTION

| NO | INSPECTION ITEMS        | SPECIFICATION   | MIN | MAX | AVERAGE | RESULT |
|----|-------------------------|-----------------|-----|-----|---------|--------|
| 11 | PLATING THICKNESS (Nip) | 2.0~4.0 $\mu$ m |     |     |         |        |
| 12 |                         |                 |     |     |         |        |
| 13 |                         |                 |     |     |         |        |
| 14 |                         |                 |     |     |         |        |

도금두께 성적서 참조

## III.FUNCTIONAL TEST

| NO | INSPECTION ITEMS          | SPECIFICATION          | TEST SAMPLE | RESULT |
|----|---------------------------|------------------------|-------------|--------|
| 15 | ADHESION TEST<br>(밀착성 시험) | Not permit the peeling |             | OK     |
| 16 |                           |                        |             |        |

| FINAL RESULT                                                                        | REMARK | PREPARED BY | CHECKED BY | APPROVED BY                                                                           |
|-------------------------------------------------------------------------------------|--------|-------------|------------|---------------------------------------------------------------------------------------|
|  |        | 고은채         |            |  |

에스코넥

Nip : 2.0~4.0 $\mu$ m

품명: DUMMY-D938468


LOT NO: 20261006-1

일자: 2026.10.06

FUNC: MEASURE  
DATE: 2026-10-06  
COL : 1.000 mm

| No    | $\mu$ m<br>NiP | NiP tolerance     |
|-------|----------------|-------------------|
| 1     | 2.950          | 2.570 2.760 2.950 |
| 2     | 2.850          |                   |
| 3     | 2.645          |                   |
| 4     | 2.572          |                   |
| 5     | 2.782          |                   |
| Mean  | 2.760          |                   |
| S.Dev | 0.137          |                   |

$\frac{\text{NiP}}{\text{Al}}$   
SEC : 15 Sec



도금원소 : NiP//Al

측정값 개수 5

최대값 2.950

최소값 2.572

범위 0.378

평균값 2.760

표준편차 0.137

변동계수 4.948

발행처 : 우리하이피

