

Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	PLATING DATE	ISSUED DATE(발행일자)
호연이엔지	HOLD DOWN PIN	20261003-1~48	2026.10.03
MATERIAL(재질)	SPEC		수량
SUS	Ni : 1.0~3.0 μ m		480,000 EA

I. VISUAL INSPECTION

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	V	6	BENT(변형)	0/1	V
2	STAIN(얼룩)	0/1	V	7	NO PLATING(미도금)	0/1	V
3	RUST(부식)	0/1	V	8			
4	CONTAMINATION(오염)	0/1	V	9			
5	PEELING(도금 벗겨짐)	0/1	V	10			


II. DIMENSION INSPECTION

NO	INSPECTION ITEMS	SPECIFICATION	MIN	MAX	AVERAGE	RESULT
11	PLATING THICKNESS (Ni)	1.0~3.0 μ m				
12						
13						
14						

도금두께 성적서 참조

III. FUNCTIONAL TEST

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
15	ADHESION TEST (밀착성 시험)	Not permit the peeling		OK
16				

FINAL RESULT	REMARK	PREPARED BY	CHECKED BY	APPROVED BY
		고은채		

호연이엔지 Ni : 1.0~3.0 μ m


품명: HOLD DOWN PIN LOT NO: 20261003-1 일자: 2026.10.03

No	μ m Ni	Ni tolerance
1	1.875	1.666 1.813 1.960
2	1.904	
3	1.897	
4	1.724	
5	1.666	
Mean	1.813	
S.Dev	0.099	

FUNC: MEASURE
DATE: 2026-10-03
COL : 0.400 mm


Au
Ni
SS

SEC : 15 Sec



도금원소 : Au/Ni//SS

측정값 개수 5
최대값 1.904
최소값 1.666
범위 0.238
평균값 1.813
표준편차 0.099
변동계수 5.444



우리하이피