



Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	LOT NO(로트번호)	ISSUED DATE(발행일자)
세종에이앤에스	0.15*175	20260605 -01 ~ 02	2026-06-05
규격(재질)		LOT SIZE(수량)	
0.15*175 Cu	Ni 1.0~2.0μm	529.2 Kg	

I. VISUAL INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/S)

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION
1	DISCOLORATION(변색)	0/1	OK	6	NO PLATING(미도금)
2	STAIN(얼룩)	0/1	OK	7	PEELING(도금 벗겨짐)
3	RUST(부식)	0/1	OK	8	LUMP(도금 뭉침)
4	CONTAMINATION(오염)	0/1	OK	9	CAMBER(휨)
5	BENT(변형)	0/1	OK	10	PLATING BURR (도금)

II. DIMENSION INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/S)

NO	항목/구분	SPEC			검사주기	우리하이피	
		규격	하한(-)	상한(+)		1차	2차
1	전폭	175.0	-0.1		Reel/Lot	174.997	
2							
3							
4							
5							
6							
7							
8							
9							
10							

III. PLATING THICKNESS(도금두께) (Sampling Plan : 1y)

NO	SPECIFICATION	Measurement Data	RESULT
1	X-Ray 측정 Ni 1.0~2.0μm	첨부 : 도금성적서	OK
		첨부 : 도금성적서	

IV. F

NO		RESULT
1		OK

제품도면		리하이피	김영란	조승현	종합판정	
		고객	작성	승인	종합판정	

업체명 : 세종에이앤에스

품명 : 0.15x175 초물 LOT NO : 260605-01 DATE : 26.06.05.


No	μm Ni	Ni tolerance		
		1.214	1.371	1.527
1	1.303			
2	1.292			
3	1.341			
4	1.390			
5	1.527			
Mean	1.371			
S.Dev	0.095			

FUNC: MEASURE
COL : 0.100 mm

$\frac{\text{Ni}}{\text{Cu}}$
SEC : 20 Sec

평균값 1.371
표준편차 0.095
변동계수 6.966

우리하이피



업체명 : 세종에이앤에스


품명 : 0.15x175 종물 LOT NO : 260605-01 DATE : 26.06.05.

No	μm Ni	Ni tolerance
1	1.297	1.260 1.359 1.458
2	1.274	
3	1.458	
4	1.370	
5	1.396	
Mean	1.359	
S.Dev	0.075	

FUNC: MEASURE
COL : 0.100 mm

$\frac{\text{Ni}}{\text{Cu}}$

SEC : 20 Sec



도금원소 : Ni//Cu
측정값 개수 5
최대값 1.458
최소값 1.274
범위 0.184
평균값 1.359
표준편차 0.075
변동계수 5.502

우리하이피

