



Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	LOT NO(로트번호)	ISSUED DATE(발행일자)
신흥 SEC	0.4*26	20260608 -01	2026-06-08
규격(재질)		LOT SIZE(수량)	
0.4*26 AL	Ni 1.5μm ~	728 Kg	

I. VISUAL INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/5Reel)

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS
1	DISCOLORATION(변색)	0/1	OK	6	NO PLATING(미도금)
2	STAIN(얼룩)	0/1	OK	7	PEELING(도금 벗겨짐)
3	RUST(부식)	0/1	OK	8	LUMP(도금 뭉침)
4	CONTAMINATION(오염)	0/1	OK	9	CAMBER(휨)
5	BENT(변형)	0/1	OK	10	PLATING BURR (도금)

6/8

0.4x26

① ㄱ ㉠ ㄱ ㉡ ㄱ
② ㄱ ㉢ ㄱ ㉣ ㄱ
③ ㄱ ㉤ ㄱ ㉥ ㄱ
④ ㄱ ㉦ ㄱ ㉧ ㄱ
⑤ ㄱ ㉨ ㄱ

총 728kg

II. DIMENSION INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/5Reel)

NO	항목/구분	SPEC			검사주기	우리하이피	
		규격	하한(-)	상한(+)		1차	2차
1	전폭	26.0	-0.1		Reel/Lot	25.944	0.403
2						25.960	0.403
3						25.960	0.403
4						25.992	0.401
5						25.997	0.403
6						25.988	0.403
7						25.970	0.402
8						25.956	0.402
9						25.958	0.403
10						25.979	0.402

III. PLATING THICKNESS(도금두께) (Sampling Plan : 1y)

NO	SPECIFICATION	Measurement Data	RESULT
1	X-Ray 측정	첨부 : 도금성적서	OK
	Ni 1.5μm ~	첨부 : 도금성적서	

IV. FUNCTIONAL TEST (Sampling Plan : n=100mm/EA, 2EA/Shipping, c=0)

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
1	ADHESION TEST (밀착성 시험)	1.제품을 스카치 Tape에 완전 밀착후 45도 각도로 순간적으로 떼어낸다.(돌돌 및 벗겨짐) 2.테이프 시험이 안되는 제품은 니퍼로 90도로 상.하각은후 도금돌돌 이나 벗겨짐이 없을것.		OK

제품도면		우리하이피	작성	승인	종합판정	
		고객	작성	승인		
			김영란	조승현		

업체명 : 신흥SEC


품명 : 0.4x26 초물 LOT NO : 260608-01 DATE : 26.06.08.

No	μm Ni	Ni tolerance
1	2.086	2.029 2.067 2.104
2	2.090	
3	2.071	
4	2.029	
5	2.056	
6	2.068	
Mean	2.067	
S.Dev	0.022	

FUNC: MEASURE
COL : 0.100 mm


$\frac{\text{Ni}}{\text{Al}}$

SEC : 15 Sec



도금원소 : Ni//Al
측정값 개수 6
최대값 2.090
최소값 2.029
범위 0.061
평균값 2.067
표준편차 0.022
변동계수 1.076

우리하이피



업체명 : 신흥SEC


품명 : 0.4x26 초물 LOT NO : 260608-14 DATE : 26.06.08.

No	μm Ni	Ni tolerance
1	2.090	2.037 2.066 2.095
2	2.076	
3	2.050	
4	2.082	
5	2.062	
6	2.037	
Mean	2.066	
S.Dev	0.020	

FUNC: MEASURE
COL : 0.100 mm

Ni
Al

SEC : 15 Sec



도금원소 : Ni//Al
측정값 개수 6
최대값 2.090
최소값 2.037
범위 0.053
평균값 2.066
표준편차 0.020
변동계수 0.979

우리하이피

