



Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	LOT NO(로트번호)	ISSUED DATE(발행일자)
신흥 SEC	0.4*26	20260618 -01	2026-06-18
규격(재질)		LOT SIZE(수량)	
0.4*26 AL	Ni 1.5μm ~	612 Kg	

I. VISUAL INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/5Reel)

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS
1	DISCOLORATION(변색)	0/1	OK	6	NO PLATING(미도금)
2	STAIN(얼룩)	0/1	OK	7	PEELING(도금 벗겨짐)
3	RUST(부식)	0/1	OK	8	LUMP(도금물짐)
4	CONTAMINATION(오염)	0/1	OK	9	CAMBER(휨)
5	BENT(변형)	0/1	OK	10	PLATING BURR (도금)

II. DIMENSION INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/5Reel)

NO	항목/구분	SPEC			검사주기	우리하이피	
		규격	하한(-)	상한(+)		1차	2차
1	전폭	26.0	-0.1		Reel/Lot	25.969	0.402
2						25.928	0.401
3						25.959	0.401
4						25.942	0.401
5						25.923	0.401
6						25.959	0.403
7						25.935	0.402
8						25.931	0.401
9						25.930	0.401
10						25.921	0.401

6/18
0.4x26
① ㄱ1 ㉕51 ㉕51
② ㄱ1 ㉕51 ㉕51
③ ㄱ1 ㉕51 ㉕51
④ ㄱ1 ㉕51 ㉕51
총 612kg

III. PLATING THICKNESS(도금두께) (Sampling Plan : 1y)

NO	SPECIFICATION	Measurement Data	RESULT
1	X-Ray 측정 Ni 1.5μm ~	첨부 : 도금성적서 첨부 : 도금성적서	OK

IV. FUNCTIONAL TEST (Sampling Plan : n=100mm/EA, 2EA/Shipping, c=0)

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
1	ADHESION TEST (밀착성 시험)	1.제품을 스카치 Tape에 완전 밀착후 45도 각도로 순간적으로 떼어낸다.(돌출 및 벗겨짐) 2.테이프 시험이 안되는 제품은 니퍼로 90도로 상.하각은후 도금돌출이나 벗겨짐이 없을것.		OK

제품도면		우리하이피	작성	승인	종합판정	
		김영란		조승현		
고객		작성		승인	종합판정	

업체명 : 신흥SEC


품명 : 0.4x26 초물 LOT NO : 260618-01 DATE : 26.06.18.

No	μm Ni	Ni tolerance
1	2.009	1.986 2.024 2.062
2	2.033	
3	2.000	
4	2.016	
5	2.024	
6	2.062	
Mean	2.024	
S.Dev	0.022	

FUNC: MEASURE
COL : 0.100 mm


Ni
—
Al

SEC : 15 Sec



도금원소 : Ni//Al
측정값 개수 6
최대값 2.062
최소값 2.000
범위 0.062
평균값 2.024
표준편차 0.022
변동계수 1.080

우리하이피



업체명 : 신흥SEC


품명 : 0.4x26 초물 LOT NO : 260618-12 DATE : 26.06.18.

No	μm Ni	Ni tolerance		
		2.013	2.040	2.067
1	2.037			
2	2.026			
3	2.055			
4	2.013			
5	2.048			
6	2.060			
Mean	2.040			
S.Dev	0.018			

FUNC: MEASURE
COL : 0.100 mm

Ni
—
Al

SEC : 15 Sec



도금원소 : Ni//Al
측정값 개수 6
최대값 2.060
최소값 2.013
범위 0.047
평균값 2.040
표준편차 0.018
변동계수 0.883

우리하이피

