



Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	LOT NO(로트번호)	ISSUED DATE(발행일자)
신흥 SEC	0.4*26	20260706 -01 ~ 12	2026-07-06
규격(재질)		LOT SIZE(수량)	
0.4*26 AL	Ni 1.5 μ m ~	616 Kg	

I. VISUAL INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/5Reel)

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION
1	DISCOLORATION(변색)	0/1	OK	6	NO PLATING(미도금)
2	STAIN(얼룩)	0/1	OK	7	PEELING(도금 벗겨짐)
3	RUST(부식)	0/1	OK	8	LUMP(도금물침)
4	CONTAMINATION(오염)	0/1	OK	9	CAMBER(휨)
5	BENT(변형)	0/1	OK	10	PLATING BURR (도금)

7/6
0.4x26
① ㄱ ⑤ ㄱ ⑩ ㄱ
② ㄱ ⑥ ㄱ ⑪ ㄱ
③ ㄱ ⑦ ㄱ ⑫ ㄱ
④ ㄱ ⑧ ㄱ ⑬ ㄱ
총 616kg

II. DIMENSION INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/5Reel)

NO	항목/구분	SPEC			검사주기	우리하이피	
		규격	하한(-)	상한(+)		1차	2차
1	전폭	26.0	-0.1		Reel/Lot	25.983	0.402
2						25.984	0.403
3						25.970	0.403
4						25.985	0.402
5						25.975	0.403
6						25.991	0.403
7						25.981	0.402
8						25.986	0.403
9						25.991	0.401
10						25.975	0.402

III. PLATING THICKNESS(도금두께) (Sampling Plan : 1y)

NO	SPECIFICATION	Measurement Data	RESULT
1	X-Ray 측정 Ni 1.5 μ m ~	첨부 : 도금성적서 첨부 : 도금성적서	OK

IV. FUNCTIONAL TEST (Sampling Plan : n=100mm/EA, 2EA/Shipping, c=0)

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
1	ADHESION TEST (밀착성 시험)	1.제품을 스카치 Tape에 완전 밀착후 45도 각도로 순간적으로 떼어낸다.(들뜸 및 벗겨짐) 2.테이프 시험이 안되는 제품은 니퍼로 90도로 상.하각은후 도금들뜸 이나 벗겨짐이 없을것.		OK

제품도면		우리하이피	작성	승인	종합판정	
		김영란		조승현		
고객		작성		승인	종합판정	

업체명 : 신흥SEC


품명 : 0.4x26 초물 LOT NO : 260706-01 DATE : 26.07.06.

No	μm Ni	Ni tolerance
1	2.064	2.019 2.065 2.111
2	2.019	
3	2.059	
4	2.072	
5	2.090	
6	2.085	
Mean	2.065	
S.Dev	0.025	

FUNC: MEASURE
COL : 0.100 mm


Ni
—
Al

SEC : 15 Sec



도금원소 : Ni//Al
측정값 개수 6
최대값 2.090
최소값 2.019
범위 0.071
평균값 2.065
표준편차 0.025
변동계수 1.230

우리하이피



업체명 : 신흥SEC


품명 : 0.4x26 초물 LOT NO : 260706-12 DATE : 26.07.06.

No	μm Ni	Ni tolerance	
		2.031	2.104
1	2.064		
2	2.075		
3	2.031		
4	2.090		
5	2.086		
6	2.058		
Mean	2.067		
S.Dev	0.022		

FUNC: MEASURE
COL : 0.100 mm

Ni
—
Al

SEC : 15 Sec



도금원소 : Ni//Al
측정값 개수 6
최대값 2.090
최소값 2.031
범위 0.059
평균값 2.067
표준편차 0.022
변동계수 1.046

우리하이피

