



Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	LOT NO(로트번호)	ISSUED DATE(발행일자)
풍산	0.1*175	63B54B0A2 01~04	2026-09-15
규격(재질)	LOT SIZE(수량)		
0.1*175 CU	Ni 1.0~2.0μm 545 Kg		

I. VISUAL INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/Shipping, c=0)

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	OK	6	NO PLATING(미도금)	0/1	OK
2	STAIN(얼룩)	0/1	OK	7	PEELING(도금 벗겨짐)	0/1	OK
3	RUST(부식)	0/1	OK	8	LUMP(도금물침)	0/1	OK
4	CONTAMINATION(오염)	0/1	OK	9	CAMBER(휨)	0/1	OK
5	BENT(변형)	0/1	OK	10	PLATING BURR (도금버)	0/1	OK

II. DIMENSION INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/Shipping, c=0)

NO	항목/구분	SPEC			검사주기	우리하이피		수량	고객		판정
		규격	하한(-)	상한(+)		1차	2차		1차	2차	
1	전폭	175.0	-0.1		Reel/Lot	175.030		149.5			OK
2						175.010		121.5			
3						174.999		120.5			
4						174.989		148.5			
5											
6											
7											
8											
9											
10											

III. PLATING THICKNESS(도금두께) (Sampling Fy


NO	SPECIFICATION		Measurement Data	RESULT
1	X-Ray 측정		첨부 : 도금성적서	OK
		Ni 1.0~2.0μm	첨부 : 도금성적서	

IV. FUNCTIONAL TEST (Sampling Plan : n=100mm/EA, 2EA/Shipping, c=0)

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
1				
제품도면		고객	합판정	


업체명 : 풍산

품명 : 0.1x175 초물 LOT NO : 63B54B0A2 DATE : 26.09.14

No	μm Ni	Ni tolerance	
		1.405	1.444 1.482
1	1.405		
2	1.455		
3	1.451		
4	1.467		
5	1.440		
Mean	1.444		
S.Dev	0.024		

FUNC: MEASURE
COL : 0.100 mm

Ni
Cu
SEC : 20 Sec



도금원소 : Ni//Cu
측정값 개수 5
최대값 1.467
최소값 1.405
범위 0.062
평균값 1.444
표준편차 0.024
변동계수 1.638

우리하이피

업체명 : 풍산


품명 : 0.1x175 중물 LOT NO : 63B54B042 DATE : 26.09.14

No	μm Ni	Ni tolerance
1	1.462	1.462 1.475 1.488
2	1.475	
3	1.482	
4	1.467	
5	1.488	
Mean	1.475	
S.Dev	0.011	

FUNC: MEASURE
COL : 0.100 mm

Ni
Cu

SEC : 20 Sec



도금원소 : Ni//Cu
측정값 개수 5
최대값 1.488
최소값 1.462
범위 0.026
평균값 1.475
표준편차 0.011
변동계수 0.720

우리하이피