



Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	LOT NO(로트번호)	ISSUED DATE(발행일자)
풍산	0.1*163	63CX5B0A11~ 외 01~04	2026-09-17
규격(재질)		LOT SIZE(수량)	
0.1*163 CU	Ni 1.0~2.0μm	836.5 Kg	

I. VISUAL INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/Shipping, c=0)							
NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	OK	6	NO PLATING(미도금)	0/1	OK
2	STAIN(얼룩)	0/1	OK	7	PEELING(도금 벗겨짐)	0/1	OK
3	RUST(부식)	0/1	OK	8	LUMP(도금물침)	0/1	OK
4	CONTAMINATION(오염)	0/1	OK	9	CAMBER(휨)	0/1	OK
5	BENT(변형)	0/1	OK	10	PLATING BURR (도금버)	0/1	OK

II. DIMENSION INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/Shipping, c=0)											
NO	항목/구분	SPEC			검사주기	우리하이피		수량	고객		판정
		규격	하한(-)	상한(+)		1차	2차		1차	2차	
1	전폭	163.0	-0.1		Reel/Lot	163.090		285.5			OK
2						163.080		298.0			
3						163.080		139.5			
4						163.090		113.5			
5											
6											
7											
8											
9											
10											

III. PLATING THICKNESS(도금두께) (Sampling Plan : n=100mm/EA, 2EA/Shipping, c=0)			
NO	SPECIFICATION	Measurement Data	RESULT
1	X-Ray 측정	첨부 : 도금성적서	OK
	Ni 1.0~2.0μm	첨부 : 도금성적서	

IV. FUNCTIONAL TEST (Sampling Plan : n=100mm/EA, 2EA/Shipping, c=0)				
NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
1	ADHESION(밀착성)			

제품도면	0.1*163 1) 63CX5B0A11 / 260915-1 2) 63CX5B0A12 / 260916-1 3) 63B54B0A2 / 260916-2 4) 63B54B0A2 / 260917-1	우리하이피	작성	승인	종합판정	합격 2026-09-17 우리하이피(주) Q.C
			심문경	조승현		
		고객	작성	승인	종합판정	

업체명 : 풍산


품명 : 0.1x163 초물 LOT NO : 63CX5B0A11 DATE : 26.09.15

No	µm Ni	Ni tolerance
1	1.446	1.438 1.474 1.510
2	1.469	
3	1.510	
4	1.447	
5	1.497	
Mean	1.474	
S.Dev	0.029	

FUNC: MEASURE
COL : 0.100 mm

Ni
Cu

SEC : 20 Sec



도금원소 : Ni//Cu
측정값 개수 5
최대값 1.510
최소값 1.446
범위 0.064
평균값 1.474
표준편차 0.029
변동계수 1.967

우리하이피

업체명 : 풍산


품명 : 0.1x163 중물 LOT NO : 63CX5B0A11 DATE : 26.09.15

No	μm Ni	Ni tolerance	
		1.449	1.501
1	1.462		
2	1.466		
3	1.501		
4	1.467		
5	1.480		
Mean	1.475		
S.Dev	0.016		

FUNC: MEASURE
COL : 0.100 mm

Ni
Cu

SEC : 20 Sec



도금원소 : Ni//Cu
측정값 개수 5
최대값 1.501
최소값 1.462
범위 0.039
평균값 1.475
표준편차 0.016
변동계수 1.080

우리하이피

