



Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	LOT NO(로트번호)	ISSUED DATE(발행일자)
세종에이앤에스	0.15*175	20260307 -01 ~ 02	2026-03-07
규격(재질)		LOT SIZE(수량)	
0.15*175 Cu	Ni 1.0~2.0μm	639.6 Kg	

I. VISUAL INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/S)

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION
1	DISCOLORATION(변색)	0/1	OK	6	NO PLATING(미도금)
2	STAIN(얼룩)	0/1	OK	7	PEELING(도금 벗겨짐)
3	RUST(부식)	0/1	OK	8	LUMP(도금물침)
4	CONTAMINATION(오염)	0/1	OK	9	CAMBER(휨)
5	BENT(변형)	0/1	OK	10	PLATING BURR (도금)

II. DIMENSION INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/S)

NO	항목/구분	SPEC			검사주기	우리하이피	
		규격	하한(-)	상한(+)		1차	2차
1	전폭	175.0	-0.1		Reel/Lot	174.997	
2							
3							
4							
5							
6							
7							
8							
9							
10							

III. PLATING THICKNESS(도금두께) (Sampling Plan : 1y)

NO	SPECIFICATION	Measurement Data	RESULT
1	X-Ray 측정	첨부 : 도금성적서	OK
	Ni 1.0~2.0μm	첨부 : 도금성적서	

IV. F		RESULT
NO		
1		OK

제품도면		리하이피	김영란	조승현	합판정	
		고객	작성	승인	종합판정	

업체명 : 세종에이앤에스

품명 : 0.15x175 초물 LOT NO : 260307-01 DATE : 26.03.07.

No	μm Ni	Ni tolerance		
		1.263	1.293	1.324
1	1.307			
2	1.315			
3	1.263			
4	1.285			
5	1.297			
Mean	1.293			
S.Dev	0.020			


FUNC: MEASURE
COL : 0.100 mm

$\frac{\text{Ni}}{\text{Cu}}$

SEC : 20 Sec

표준편차 0.020
변동계수 1.575

우리하이피



업체명 : 세종에이앤에스


품명 : 0.15x175 종물 LOT NO : 260307-01 DATE : 26.03.07.

No	μm Ni	Ni tolerance
1	1.244	1.233 1.277 1.321
2	1.267	
3	1.311	
4	1.321	
5	1.243	
Mean	1.277	
S.Dev	0.037	

FUNC: MEASURE
COL : 0.100 mm

$\frac{\text{Ni}}{\text{Cu}}$

SEC : 20 Sec



도금원소 : Ni//Cu
측정값 개수 5
최대값 1.321
최소값 1.243
범위 0.078
평균값 1.277
표준편차 0.037
변동계수 2.887

우리하이피

