



Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	LOT NO(로트번호)	ISSUED DATE(발행일자)
세종에이앤에스	0.15*175	20260309 -01 ~ 02	2026-03-09
규격(재질)		LOT SIZE(수량)	
0.15*175 Cu	Ni 1.0~2.0μm	640.6 Kg	

I. VISUAL INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/S)

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION
1	DISCOLORATION(변색)	0/1	OK	6	NO PLATING(미도금)
2	STAIN(얼룩)	0/1	OK	7	PEELING(도금 벗겨짐)
3	RUST(부식)	0/1	OK	8	LUMP(도금물침)
4	CONTAMINATION(오염)	0/1	OK	9	CAMBER(휨)
5	BENT(변형)	0/1	OK	10	PLATING BURR (도금)

II. DIMENSION INSPECTION (Sampling Plan : n=100mm/Reel, 5Reel/Shipping or n=50ea/S)

NO	항목/구분	SPEC			검사주기	우리하이피	
		규격	하한(-)	상한(+)		1차	2차
1	전폭	175.0	-0.1		Reel/Lot	174.999	
2							
3							
4							
5							
6							
7							
8							
9							
10							

III. PLATING THICKNESS(도금두께) (Sampling Plan : 1y)

NO	SPECIFICATION	Measurement Data	RESULT
1	X-Ray 측정 Ni 1.0~2.0μm	첨부 : 도금성적서	OK
		첨부 : 도금성적서	

NO		RESULT
1		OK

제품도면		리하이피	김영란	조승현	합판정	
		고객	작성	승인	종합판정	

업체명 : 세종에이앤에스

품명 : 0.15x175 초물 LOT NO : 260309-01 DATE : 26.03.09.

No	μm Ni	Ni tolerance	
		1.142	1.332 1.521
1	1.208		
2	1.235		
3	1.435		
4	1.521		
5	1.259		
Mean	1.332		
S.Dev	0.138		


FUNC: MEASURE
COL : 0.100 mm

$\frac{\text{Ni}}{\text{Cu}}$

SEC : 20 Sec

표준편차 0.138
변동계수 10.382

우리하이피




업체명 : 세종에이앤에스

품명 : 0.15x175 종물 LOT NO : 260309-01 DATE : 26.03.09.

No	μm Ni	Ni tolerance
1	1.272	1.272 1.353 1.434
2	1.328	
3	1.334	
4	1.403	
5	1.428	
Mean	1.353	
S.Dev	0.063	

FUNC: MEASURE
COL : 0.100 mm

$\frac{\text{Ni}}{\text{Cu}}$
SEC : 20 Sec



도금원소 : Ni//Cu
측정값 개수 5
최대값 1.428
최소값 1.272
범위 0.156
평균값 1.353
표준편차 0.063
변동계수 4.626

우리하이피

