

Quality Assurance Report

CUSTOMER(고객명)	DESCRIPTION(품명)	PLATING DATE(도금일자)	ISSUED DATE(발행일자)
쥬디울	SAMPLE	2026.08.25-01	2026.08.25
MATERIAL(재질)			수량
Brass	Ni: 2.0~6.0 μ m Ag: 0.5~1.5 μ m		52 EA

NO	INSPECTION ITEMS	Ac/Re	RESULT	NO	INSPECTION ITEMS	Ac/Re	RESULT
1	DISCOLORATION(변색)	0/1	V	6	BENT(변형)	0/1	V
2	STAIN(얼룩)	0/1	V	7	NO PLATING(미도금)	0/1	V
3	RUST(부식)	0/1	V	8			
4	CONTAMINATION(오염)	0/1	V	9			
5	PEELING(도금 벗겨짐)	0/1	V	10			


II.DIMENSION INSPECTION

NO	INSPECTION ITEMS	SPECIFICATION	MIN	MAX	AVERAGE	RESULT
11	PLATING THICKNESS (Ni)	2.0~6.0 μ m				
12	PLATING THICKNESS (Ag)	0.5~1.5 μ m				
13						
14						

도금두께 성적서 참조

III.FUNCTIONAL TEST

NO	INSPECTION ITEMS	SPECIFICATION	TEST SAMPLE	RESULT
15	ADHESION TEST (밀착성 시험)	Not permit the peeling		OK
16				

FINAL RESULT	REMARK	PREPARED BY	CHECKED BY	APPROVED BY
		문명선		

쥬디올

Ni: 2.0~6.0 μ m Ag: 0.5~1.5 μ m

품명: SAMPLLE LOT NO: 260825-01



일자: 2026.08.25

No	μ m Ag	μ m Ni	Ag tolerance		
			1.037	1.087	1.137
1	1.110	2.989			
2	1.114	2.968			
3	1.086	2.698			
4	1.037	2.740			
5	1.087	2.514			
Mean	1.087	2.782			
S.Dev	0.027	0.178			

FUNC: MEASURE
DATE: 2026-08-25
COL : 1.000 mm

Ag
Ni
Cu

SEC : 15 Sec



도금원소 : Ag/Ni//Cu

측정값 개수	5	5
최대값	1.114	2.989
최소값	1.037	2.514
범위	0.077	0.475
평균값	1.087	2.782
표준편차	0.027	0.178
변동계수	2.523	6.392

우리하이피

